



Universiteit
Leiden
The Netherlands

Low-energy electron microscopy on two-dimensional systems : growth, potentiometry and band structure mapping

Kautz, J.

Citation

Kautz, J. (2015, April 30). *Low-energy electron microscopy on two-dimensional systems : growth, potentiometry and band structure mapping*. *Casimir PhD Series*. Retrieved from <https://hdl.handle.net/1887/32852>

Version: Corrected Publisher's Version

License: [Licence agreement concerning inclusion of doctoral thesis in the Institutional Repository of the University of Leiden](#)

Downloaded from: <https://hdl.handle.net/1887/32852>

Note: To cite this publication please use the final published version (if applicable).

Cover Page



Universiteit Leiden



The handle <http://hdl.handle.net/1887/32852> holds various files of this Leiden University dissertation

Author: Kautz, Jaap

Title: Low-energy electron microscopy on two-dimensional systems : growth, potentiometry and band structure mapping

Issue Date: 2015-04-30

Low-Energy Electron Microscopy on Two-Dimensional Systems:

Growth, Potentiometry and Band Structure Mapping

Proefschrift

ter verkrijging van
de graad van Doctor aan de Universiteit Leiden,
op gezag van Rector Magnificus prof.mr. C.J.J.M. Stolker,
volgens besluit van het College voor Promoties
te verdedigen op donderdag 30 april 2015
klokke 15:00 uur

door

Jaap Kautz

geboren te Woerden
in 1982

Promotiecommissie:

Promotores: Prof.dr. J.M. van Ruitenbeek

Prof.dr. R.M. Tromp

Co-Promotor: Dr.ir. S.J. van der Molen

Overige leden: Prof.dr.ir. P. Kruit (Technische Universiteit Delft)
Dr. F.-J. Meyer zu Heringdorf (Universität Duisburg-Essen, Duitsland)
Prof.dr.ir. H.J.W. Zandvliet (Universiteit Twente)
Dr. M.P. Allan
Prof.dr. E.R. Eliel
Dr. I.M.N. Groot
Prof.dr. J. Zaanen

Casimir PhD series, Delft-Leiden 2015-09

ISBN 978-90-85932178

An electronic version of this thesis can be found at

<https://openaccess.leidenuniv.nl>.

The work described in this thesis is supported by the Netherlands Organisation for Scientific Research (NWO) via a Vidi grant (680-47-502) and an NWO-Groot grant.

Part of this research is supported by the “Physics in 1D” program of the Foundation for Fundamental Research on Matter (FOM), which is part of the Netherlands Organisation for Scientific Research (NWO).

The cover shows an artist’s impression of the potential map in Fig. 5.4.

Preface

Most textbooks on Low-Energy Electron Microscopy (LEEM), will start by describing it as the ideal tool for surface science. And while it is true that the short mean free path of the low-energy electrons makes the technique very suitable to study surface structures, the focus of the LEEM community has significantly broadened over the years. What started out as a technique with a narrow field of application quickly grew into a versatile many-purpose research tool. It is one of the goals of this work to extend the applicability of LEEM in condensed matter physics even further.

The insight that LEEM can be used for more than surface science is not new. Already since the creation of the first LEEM by Teliëps and Bauer^[1] it was clear that there was a relation between the electron reflectivity and electronic states in the studied system. Still, for a long time there has been a focus on the analysis of surface structures. This is mainly because of the ample opportunities available for LEEM in this field of research. The invention of LEEM suddenly gave direct access to the dynamics of surface processes, which up till then only could be inferred. Many fundamental surface science problems, like the dynamics of surface reconstructions and layer growth, could suddenly be solved due to the direct visualization by LEEM^[2-4]. However, these early successes sparked an increased interest in LEEM and as the LEEM community grew, its scope would broaden.

Parallel to the physics research, there has been a lot of work on the improvement of the spatial resolution of LEEM instruments. Where the first instruments had a resolution of ≈ 20 nm^[1], the present day optimal resolution, as obtained in the Leiden ESCHER set-up described in chapter 1, is 1.4 nm. One key ingredient that enabled the enormous improvement in resolution is the implementation of aberration correction. Aberration correction, which was already applied in Transmission Electron Microscopy (TEM) by the use of a series of monopoles^[5], was introduced for LEEM on the basis of an electrostatic mirror^[6-8]. Aberration correction alone has improved the resolution of LEEM by a factor 5^[9].

Technical developments have also played a great role in the diverging of LEEM applications from pure surface science. The broadening of the scope of LEEM went hand in hand with the development of new imaging meth-

ods. One big step in this evolution was the implementation of energy filters in LEEM instruments. This made it possible to combine LEEM, Low-Energy Electron Diffraction (LEED), Angle Resolved Photo-Emission Electron Microscopy (ARPES) and Electron Energy Loss Spectroscopy (EELS) measurements in one instrument, a unprecedented combination of powerful surface analysis tools.

The development of new LEEM-based techniques is still ongoing. The realization of spin-polarized electron sources with an ever increasing polarization^[10] has opened the road for the study of magnetic domains^[11,12]. Moreover, the development of so-called pump-probe experiments allows analysis of dynamics on femtosecond timescales^[13,14]. In this work we add yet two more techniques to this already broad repertoire of analysis tools.

This thesis starts with an introduction of LEEM in general, the various available imaging modes and a description of our aberration-corrected ES-CHEM set-up in chapter 1. The rest of this thesis consists of two parts which follow a similar pattern as the history of LEEM. In the first part (chapters 2 and 3) we will use LEEM in the traditional way to study growth and analyze surface structures. Chapters 4 to 6 form the second part, where we move away from pure surface science and introduce two new LEEM techniques.

We start by investigating (sub)monolayers of Au on Si(111) in chapter 2. Specifically, we study the (5x2) structure, which is formed at low Au coverages and exhibits metallicity in only one direction. There has been a lot of controversy over the exact atomic configuration of this surface structure^[15-17]. Our results show that the number of Au atoms per unit cell is different than previously assumed and that a revision of the structural model is necessary. In chapter 3, we analyze how alkanethiols react with the (sub)monolayers of Au on Si(111), studied in chapter 2. The growth of alkanethiols on bulk Au crystals has been studied extensively^[18-20]. The stability of the self-assembled monolayers that form is mainly due to the strength of the S-Au bond^[19]. Based on the results obtained on bulk crystals one would naively expect that when submonolayers of Au are exposed to alkanethiols, the alkanethiols will react with those areas of the surface with the highest Au concentration. Surprisingly, our results show something completely different.

In the second part of this thesis, we introduce two new techniques. First, in chapter 4, we demonstrate a completely new method to analyze electron transport using LEEM. Electron transport measurements are typically performed in a two- or four-probe configuration. This allows one to perform average conductivity measurements, but local variations in conductivity are lost. By employing low-energy electrons to locally probe the electric potential, while applying an in-plane bias voltage, we are able to create potential

maps of the surface. This enables us to locally probe the conduction properties of a sample. We demonstrate our new technique, coined Low-Energy Electron Potentiometry (LEEP), by visualizing Schottky behavior at the Au-Si interface. In chapter 5, we show that for layered materials, the sensitivity of LEEP can be drastically improved. The coupling of the imaging electrons to interlayer states causes pronounced features in the energy dependence of the reflectivity^[21,22]. We can use these features to improve the accuracy of the local potential measurements. Finally, in the last chapter, we study the influence of non-normal incidence on our potentiometry results. Interestingly, we find that we can use the in-plane-momentum dependence of the electron reflectivity to obtain information on the interlayer states. This allowed us to map out the band structure of these unoccupied interlayer states in graphene. We expect this technique to be particularly useful for the analysis of van der Waals materials^[23]. With these new techniques, in combination with the already wide range of existing analysis tools, LEEM provides an unparalleled experimental set-up for complete in-situ sample characterization.

Jaap Kautz
Leiden, March 2015

References

- [1] W. Telieps and E. Bauer, *An analytical reflection and emission UHV surface electron microscope*, Ultramicroscopy **17**, 57 (1985).
- [2] E. Bauer, *Low energy electron microscopy*, Reports on Progress in Physics **57**, 895 (1994).
- [3] R. M. Tromp, *Low-energy electron microscopy*, IBM Journal of Research and Development **44**, 503 (2000).
- [4] M. S. Altman, *Trends in low energy electron microscopy.*, Journal of physics. Condensed matter : an Institute of Physics journal **22**, 084017 (2010).
- [5] R. Erni, *Aberration-Corrected Imaging in Transmission Electron Microscopy: an Introduction* (Imperial College Press, 2010).
- [6] G. F. Rempfer, D. M. Desloge, W. P. Skoczylas, and O. H. Griffith, *Simultaneous correction of spherical and chromatic aberrations with an electron mirror: An electron optical achromat*, Microscopy and Microanalysis **3**, 14 (1997).
- [7] P. Hartel, D. Preikszas, R. Spehr, H. Müller, and H. Rose, *Mirror Corrector for Low-Voltage Electron Microscopes*, Advances in Imaging and Electron Physics **120**, 41 (2002).
- [8] R. M. Tromp, J. B. Hannon, A. W. Ellis, W. Wan, A. Berghaus, and O. Schaff, *A new aberration-corrected, energy-filtered LEEM/PEEM instrument. I. Principles and design.*, Ultramicroscopy **110**, 852 (2010).
- [9] S. M. Schramm, A. B. Pang, M. S. Altman, and R. M. Tromp, *A Contrast Transfer Function approach for image calculations in standard and aberration-corrected LEEM and PEEM.*, Ultramicroscopy **115**, 88 (2012).
- [10] N. Yamamoto, T. Nakanishi, A. Mano, Y. Nakagawa, S. Okumi, M. Yamamoto, T. Konomi, X. Jin, T. Ujihara, Y. Takeda, et al., *High brightness and high polarization electron source using transmission photocathode with GaAs-GaAsP superlattice layers*, Journal of Applied Physics **103**, 064905 (2008).
- [11] H. Poppa, E. Bauer, and H. Pinkvos, *SPLEEM of Magnetic Surfaces and Layered Structures.*, MRS Bulletin pp. 38–40 (1995).

-
- [12] N. Rougemaille and A. K. Schmid, *Magnetic imaging with spin-polarized low-energy electron microscopy*, The European Physical Journal Applied Physics **50**, 20101 (2010).
- [13] F.-J. Meyer zu Heringdorf, L. I. Chelaru, S. Möllenbeck, D. Thien, and M. Horn-von Hoegen, *Femtosecond photoemission microscopy*, Surface Science **601**, 4700 (2007).
- [14] B. J. Siwick, J. R. Dwyer, R. E. Jordan, and R. J. D. Miller, *An Atomic-Level View of Melting Using Femtosecond*, Science **302**, 1382 (2003).
- [15] W. Swiech, E. Bauer, and M. Mundschau, *A low-energy electron microscopy study of the system Si (111) -Au*, Surface Science **253**, 283 (1991).
- [16] L. D. Marks and R. Plass, *Atomic structure of Si (111)-(5 2)-Au from high resolution electron microscopy and heavy-atom holography*, Physical review letters **75**, 2172 (1995).
- [17] S. C. Erwin, I. Barke, and F. J. Himpsel, *Structure and energetics of Si(111)-(5x2)-Au*, Physical Review B **80**, 155409 (2009).
- [18] G. E. Poirier, *Characterization of Organosulfur Molecular Monolayers on Au(111) using Scanning Tunneling Microscopy.*, Chemical reviews **97**, 1117 (1997).
- [19] C. Vericat, M. E. Vela, G. Benitez, P. Carro, and R. C. Salvarezza, *Self-assembled monolayers of thiols and dithiols on gold: new challenges for a well-known system.*, Chemical Society reviews **39**, 1805 (2010).
- [20] H. Häkkinen, *The gold-sulfur interface at the nanoscale.*, Nature chemistry **4**, 443 (2012).
- [21] H. Hibino, H. Kageshima, F. Maeda, M. Nagase, Y. Kobayashi, and H. Yamaguchi, *Microscopic thickness determination of thin graphite films formed on SiC from quantized oscillation in reflectivity of low-energy electrons*, Physical Review B **77**, 075413 (2008).
- [22] N. Srivastava, Q. Gao, M. Widom, R. M. Feenstra, S. Nie, K. F. McCarty, and I. V. Vlassiouk, *Low-energy electron reflectivity of graphene on copper and other substrates*, Physical Review B **87**, 245414 (2013).
- [23] A. K. Geim and I. V. Grigorieva, *Van der Waals heterostructures.*, Nature **499**, 419 (2013).

Contents

Preface	i
References	iv
1 Introduction to Low-Energy Electron Microscopy	1
1.1 Introduction	3
1.2 Imaging Modes	3
1.2.1 Low-Energy Electron Microscopy	3
1.2.2 Low-Energy Electron Diffraction	5
1.2.3 Combining Real-Space and Reciprocal-Space Information	7
1.2.4 PEEM	11
1.3 The ESCHER setup	11
1.3.1 Aberration Correction	13
1.3.2 Resolution	14
1.3.3 Cryogenic LEEM	16
References	18
2 Titration of submonolayer Au growth on Si(111)	21
2.1 Introduction	23
2.2 Experimental Methods	24
2.3 Results	26
2.4 Discussion	32
2.5 Conclusions	34
References	35
3 Differential reactivity of alkanethiols with Si(111)-Au 2D surface alloys	39
3.1 Introduction	41
3.2 Experimental Methods	42
3.3 Results and Discussion	42
3.4 Conclusions	47
References	48

4 Potentiometry in LEEM	51
4.1 Introduction	53
4.2 From Potential Map to Conductivity	54
4.3 Potentiometry in LEEM	55
4.4 Design	56
4.4.1 Sample Holder	58
4.4.2 Electronics	60
4.5 Sample Preparation	62
4.5.1 High-Temperature Electrodes	62
4.5.2 Chemical Cleaning	66
4.6 M-LEEP Results	69
4.6.1 Intrinsic Potential Differences of the Si(111) Surface . .	69
4.6.2 Electron Transport Through a Au-Si-Au Junction . . .	71
4.7 Conclusions	74
4.8 Outlook: Other LEEP Techniques	74
4.8.1 Resonant Low-Energy Electron Potentiometry	74
4.8.2 Gradient Low-Energy Electron Potentiometry	76
4.8.3 Phase Coherent Potentiometry	76
References	79
5 Resonant Low-Energy Electron Potentiometry: Contactless Imaging of Charge Transport on the Nanoscale	83
5.1 Introduction	85
5.2 Experimental Methods and Results	85
5.2.1 Resonant Coupling	86
5.2.2 Counting Layers	87
5.2.3 Potentiometry	88
5.3 Discussion	91
5.4 Conclusions	93
References	94
6 Beam-Tilt Analysis and Band Structure Mapping of Unoccupied States	97
6.1 Introduction	99
6.2 Lateral-Field Influence	100
6.2.1 Simulation Method	100
6.2.2 Simulation Results	100
6.2.3 Discussion of Simulation Results	104
6.3 Angular Dependence of the Reflectivity of Few-Layer Graphene	104
6.3.1 Theory	104

6.3.2	Results	107
6.3.3	Discussion	114
6.3.4	Relevance for Potentiometry	114
6.4	Conclusions	115
	References	116
A	Electronic circuits	119
	Summary	123
	Samenvatting	127
	Curriculum Vitae	131
	List of Publications	133
	Acknowledgements	135

