Universiteit
Leiden
The Netherlands

An old problem in a new light: elemental and lead isotopic analysis of Luristan Bronzes

Oudbashi, O.; Rademakers, F.W.; Vanhaecke, F.; Degryse, P.A.I.H.; Hasanpour, A.; Bahadori, S.

Citation

Oudbashi, O., Rademakers, F. W., Vanhaecke, F., Degryse, P. A. I. H., Hasanpour, A., & Bahadori, S. (2021). An old problem in a new light: elemental and lead isotopic analysis of Luristan Bronzes. *Journal Of Archaeological Science Reports*, 39.
doi:10.1016/j.jasrep.2021.103163

Version: Not Applicable (or Unknown)

License: [Leiden University Non-exclusive license](#)

Downloaded from: <https://hdl.handle.net/1887/3256981>

Note: To cite this publication please use the final published version (if applicable).

An Old Problem in a New Light: Elemental and Lead Isotopic Analysis of Luristan Bronzes

Omid Oudbashi^{1*}

Frederik W. Rademakers^{2,3}

Frank Vanhaecke⁴

Patrick Degryse^{2,5}

Ata Hasanpour⁶

Sepehr Bahadori¹

¹Department of Conservation of Cultural and Historical Properties, Art University of Isfahan, Iran

²Department of Earth and Environmental Sciences, KU Leuven, Belgium

³Department of Scientific Research, British Museum, United Kingdom

⁴Atomic & Mass Spectrometry – A&MS Research Unit, Department of Chemistry, Ghent University, Belgium

⁵Faculty of Archaeology, Leiden University, The Netherlands

⁶Organization of Cultural Heritage, Tourism and Handicraft of Lorestan Province, Khorramabad, Iran

* Corresponding Author: o.oudbashi@au.ac.ir

An Old Problem in a New Light: Elemental and Lead Isotopic Analysis of Luristan Bronzes

Abstract

The emergence and provenance of the Luristan Bronzes has been a subject of interest for many decades. This paper presents the results of elemental and lead isotopic analysis of a series of Luristan Bronzes discovered from recent excavations in the Sangtarashan sanctuary, as well as an extensive comparative study on technology and provenance of the Luristan Bronzes. This study was performed in order to better understand tin bronze production technology in the Luristan region during the Iron Age. It focuses on the artefacts themselves, as no mining or production evidence has been discovered in Luristan so far. For this purpose, 46 samples from different pieces of thin sheet vessels from Sangtarashan were analysed by inductively coupled plasma-optical emission spectroscopy (ICP-OES) for their elemental composition and by multi-collector inductively coupled plasma-mass spectroscopy (MC-ICP-MS) for their lead isotopic composition. The results of elemental analysis showed that tin bronze with variable tin content was used to produce these artefacts. The comparative study of the alloy composition also shows that tin bronze may have been the main material to produce ritual artefacts during the Iron Age of western Iran. Furthermore, the lead isotope ratios of the Sangtarashan artefacts partially overlap with those of different copper ore deposits on the Iranian Plateau, including deposits close to Luristan (such as Deh Hosein) and ore deposits further away, in central and eastern Iran. In fact, the results revealed that it is not possible at this stage in the research to identify one specific ore deposit or region as the source of copper for tin bronze metallurgy during the Iron Age of Luristan. Thus, the research suggests that ancient metalworkers apparently used different copper sources to produce the bronze artefacts specific to the region of Luristan in western Iran.

Keywords

Luristan Bronzes, Sangtarashan sanctuary, Iron Age, Tin bronze, Alloying, Provenance analysis

Introduction

For a century, the Luristan Bronzes have been an enigma in the prehistoric archaeology of the Near East. Although they appeared in 1920's on the antiquities market in the western world as artefacts attributed to an ancient region in western Iran, namely Luristan (Overlaet, 2006; Muscarella, 1988: 112; Muscarella, 1990: 478; Moorey, 1964:72), their archaeological context remained unknown until about the 1960s and 1970s, when it was illuminated by a number of archaeological excavations of necropoli, particularly by the Belgian Archaeological Mission in Iran (BAMI) under supervision of Louis Vanden Berghe in Pusht-i Kuh, Luristan (Haerinck and Overlaet, 2004a; Haerinck, 2009; Muscarella, 1988). Various historical and archaeological studies and excavations during the 1930s up to the 1970s in western Iran and central Zagros has led to some level of understanding of the probable origins of the Luristan Bronzes (e.g., Schmidt et al., 1989; Calmeyer, 1969; Godard, 1931; Goff, 1968; Moorey, 1969; Muscarella, 1988a; 1988b; Vanden Berghe, 1971; 1981; 1987; Haerinck and Overlaet 1998; 1999; 2004b; Haerinck et al., 2004). One important issue in the archaeology of the Luristan Bronzes is that the majority of artefacts attributed to this region in museums worldwide have not been obtained from controlled excavations, but rather from illegal activities, and thus their origin cannot be confirmed (Overlaet, 2004; 2005; 2006). It should be noted that the artefacts discovered from earlier archaeological excavations are not numerous (Muscarella, 1988a; 1990). Examples include Luristan Bronzes excavated from Surkh Dum, an Iron Age sanctuary (Schmidt et al., 1989; Overlaet, 2011), War Kabud graveyards (Haerinck and Overlaet, 2004a) and Baba Jan (Goff, 1968). Of course, recent archaeological work in the Luristan region has led to the discovery of significant numbers of bronzes in particular from Sangtarashan and Baba Jilan (Hashemi et al., 2021; Hasanpur et al., 2015). Careful assessment of archaeological excavations in ancient Luristan showed that the Luristan Bronzes are artefacts of ritual significance that have been deposited in graves and sanctuaries during the Iron Age, ca. 1500-500 BCE, or according to more recent dating, ca. 1300-650 BCE in western Iran (Overlaet, 2004; 2005; 2006). Still, there are some unanswered (or incompletely answered) questions about the Luristan Bronzes such as: Which peoples or tribes manufactured these artefacts? Where were they produced? What

1 was the metallurgical technology underlying their production? Which ore resources
2 provided the raw materials, i.e., tin and copper, for the production of these artefacts? Of
3 course, it should be mentioned that a series of archaeological and analytical studies have
4 been undertaken during recent decades to address these questions (e.g., Fleming et al.,
5 2005; 2006; Oudbashi and Davami, 2014; Oudbashi and Hasanpour 2018; Oudbashi et al.,
6 2016a; Nezafati, 2006; Moorey, 1964), but the technology and provenance of tin bronze
7 production in the Iron Age of Luristan remains an underresearched topic in the archaeology
8 of prehistory on the Iranian Plateau.

9 The aims of this paper are first to offer a preliminary overview of the technology of tin
10 bronze production in the Iron Age of western Iran with particular reference to Luristan, and
11 secondly to study the metallurgy of the excavated Sangtarashan bronzes and their
12 provenance. The technological study is based, in part, on the chemical analysis of a series
13 of bronze artefacts from the Sangtarashan sanctuary and its comparison to the available
14 data on other artefacts from Luristan and elsewhere in the wider region. Provenance is
15 assessed using lead isotopic analysis of a group of the Sangtarashan artefacts and by
16 comparison with available lead isotope ratio data from other artefacts from prehistoric sites
17 and ore deposits on the Iranian Plateau. Thus, this paper aims to shed new light on tin
18 bronze technology in Luristan during the Iron Age by combining new and already available
19 analytical data.

21 **Sangtarashan Archaeological Site**

22 Recent archaeological research in the Pish-i Kuh region of Luristan (Figure 1a and 1b) has
23 led to the identification of new Iron Age sites, such as Sangtarashan and Baba Jilan, at
24 which metal artefacts were discovered including different types attributed to the Luristan
25 Bronzes' style such as vessels, finials, weapons and decorative artefacts (Hashemi et al.,
26 2021; Oudbashi et al., 2013; Malekzadeh et al., 2017; Hasanpur et al., 2015).
27 Sangtarashan is located southeast of Khorramabad, the capital of the modern Lorestan
28 province (Figure 1b). The Sangtarashan (or Patakht-e Sangtarashan) site is located at the
29 north of the Sangtarashan village in the Papi district of Khorramabad county (geographic
30 coordinates 33° 15' 15" N and 48° 33' 748" E), about 50 km southeast of Khorramabad city

(Figure 2a). It lies 1650 m above sea level in the southern part of the Luristan's Pish-i Kuh region. The archaeological site is located in a flat farming area on the southern slope of a mountain. Farming activities have covered the archaeological remains over time with a partially thick layer of dark soil. The area of the archaeological site is estimated to be around one hectare (Figure 2b). It has been excavated in six seasons from 2006 to 2011, which has led to the discovery of an Iron Age sanctuary constructed from stone fragments (Figure 2b and 2c) in which numerous metallic artefacts attributed to the Luristan Bronzes were found. The excavation site report is soon to be published by Dr. Zahra Hashemi and colleagues (Dr. Ata Hasanpour and Dr. Mehrdad Malekzadeh) and earlier preliminary publications on the excavations include: Oudbashi et al., 2013; Oudbashi et al., 2016a; Malekzadeh et al., 2017; 2018; Hasanpur and Malekzadeh, 2019). Archaeological excavations yielded no evidence of graves, but rather, more than 2000 diverse metal artefacts attributed to the Luristan Bronzes' style, ranging in character from simple to sophisticated types. These were all found associated with several architectural structures at the site (Figure 3) (Malekzadeh et al., 2017; Oudbashi et al., 2013). Also, results of ^{14}C dating on two animal bone samples from the site provided two dates of ca. 15th-14th and late 9th- early 8th centuries BCE i.e., ranging from Iron Age I to early Iron Age III (Hashemi et al., 2021). Archaeological finds including the metal artefacts and the simple stone architecture suggest that the site's main period of activity is Iron Age II-III. Accordingly, the site has been identified as an Iron Age II-III sanctuary and is compared with the only other known Iron Age sanctuary site discovered in Luristan, in the Pish-i Kuh, namely Surkh Dum (or Surkh Dum-e Lori), excavated by E. F. Schmidt in the 1930s (Schmidt et al., 1989).

The metal artefacts from Sangtarashan include different types made of a tin bronze alloy that represent well the variability in elemental composition of the Luristan Bronzes. In total 2349 artefacts were found in Sangtarashan during the six seasons of excavation as associated groups (caches) or as scattered finds. One hundred and two artefacts, mainly metallic, were found in sixteen caches (Figure 3a and 3b). The rest (2247 artefacts), belonged to the second group, that of scattered finds. A significant number of the excavated

1 artefacts were metallic artefacts, including numerous bronzes and some iron artefacts
2 (Malekzadeh et al., 2017; 2018; Hasanpur and Malekzadeh, 2019).
3 Some artefacts from Sangtarashan were analysed by microscopic and elemental analysis
4 methods, showing that binary tin bronze alloys were used to produce these artefacts
5 (Oudbashi et al., 2013; Oudbashi and Davami, 2014; Oudbashi et al., 2016a). Furthermore,
6 as noted above, other artefacts from the Luristan Bronzes collection from different
7 archaeological sites or unprovenanced collections were analysed by various researchers
8 using different elemental analysis and microscopic methods to understand the alloy
9 composition and manufacturing methods. The data reported clarified some technological
10 aspects of this invaluable metal collection, such as strongly variable tin concentrations in
11 similar artefacts. Nevertheless, the technology of tin bronze metallurgy of the Luristan
12 Bronzes and the provenance of the raw materials used has not been studied widely and the
13 Sangtarashan collection provides a rare opportunity to perform an extensive analytical
14 study on the technology and provenance of the Luristan Bronzes.

16 **Materials and Methods**

17 *Samples*

18 A total of 46 samples from 31 broken metal vessels excavated during different seasons of
19 the Sangtarashan excavation were selected (Figure 4). These vessels are broken artefacts
20 that could be sampled easily by cutting a small fragment from broken pieces using a
21 jeweller's saw. The very thin corrosion crust from the surface was mechanically removed
22 before further treatment of each sample. These corrosion crusts were studied previously and
23 revealed to be very thin (less than 100 μm overall) without indications of active corrosion
24 in the burial environment such as significant amounts of chlorine (Oudbashi et al., 2016b;
25 Oudbashi, 2018). The samples include vessel edges (7 samples), bodies (29 samples),
26 spouts (3 samples), a base (one sample) and a handle (one sample) and other types of
27 metallic pieces, such as a simple pin or rod (one sample) and shield pins (4 samples).
28 Sample details are presented in Table 1. In some vessels, the body and the edge were both
29 selected for analysis because the artefact was heavily fragmented and transformed into
30 many pieces and, in many cases, the appearance of the edges and bodies was different

1 enough to suggest that these pieces may originate from different artefacts (e.g., ST.10-10
2 and ST.20-10 see Table 1) although other artefacts show similar appearance in their pieces
3 including edge and body (e.g., ST.01-10, ST.03-10, ST.04-10 and ST.08-10, see Table 1).
4 Other pieces such as pins, spouts and handles are obviously made of separate pieces (e.g.,
5 ST.02-10, ST.18-10 and ST-KH, see Table 1). Some of the samples were previously
6 analysed by elemental analysis methods such as Inductively Coupled Plasma – Optical
7 Emission Spectroscopy (ICP-OES) and Scanning Electron Microscopy – Energy Dispersive
8 Spectroscopy (SEM-EDS) (Oudbashi et al., 2013; Oudbashi and Davami, 2014; Oudbashi
9 et al., 2016a), but some others have not been analysed before (10 samples) and their
10 compositions are reported for the first time here. Nevertheless, all samples were analysed
11 here again to obtain comparable results, as the majority of previous results were obtained
12 by semi-quantitative SEM-EDS whereby trace elements were not determined.

14 *Analytical Methods*

15 To identify the elemental composition of the metal artefacts, quantitative elemental analysis
16 was performed using ICP-OES to determine the concentrations of major, minor and trace
17 elements. The detection limit of the method was 0.001 weight percent (wt.%). For the
18 purpose of ICP-OES analysis, about 0.5 g of the metallic core of each artefact was taken
19 and the corrosion layer was removed mechanically. Subsequently, the sample was first
20 dissolved in pure aqua regia (HCl + HNO₃, 3:1) and then diluted after complete dissolution.
21 The solution thus obtained was measured using a Varian 735 model ICP-OES instrument in
22 operation at the Zarazma Mineral Studies Company, Tehran.

23 Separate samples (ca. 0.05 g) from the same artefacts were dissolved for lead isotopic
24 analysis at the Geochemical Laboratory of KU Leuven (Belgium). Dissolved samples were
25 taken to a class-10 clean lab facility at Ghent University (Belgium) for chromatographic
26 lead isolation (De Muynck et al. 2008) relying on the use of Pb-SPEC resin (Eichrom
27 Technologies). Single-collector ICP-MS was used to determine the Pb concentration to
28 evaluate target element recovery and allow adequate dilution, such that the Pb
29 concentration (150 µg/kg) in all sample and standard solutions measured matched within ±
30 12%. Lead isotope ratios were determined using a Thermo Scientific Neptune Multi-

Collector – Inductively Coupled Plasma – Mass Spectrometer (MC-ICP-MS) in operation at Ghent University. The bias introduced by instrumental mass discrimination was corrected for by using a combination of internal correction (with Tl as an internal standard and following Russell’s law) and external correction, based on replicate sample-standard bracketing measurements of the NIST SRM 981 common lead standard (using the commonly accepted isotope ratio values from Galer and Abouchami (1998). Full details for sample preparation and analytical procedures are provided in Rademakers et al. (2020). Relative errors (σ , calculated from 60 replicate measurements) on the data presented here are better than 0.02% for the corrected ratios to ^{204}Pb , and better than 0.005% for ratios to ^{206}Pb .

Results and Discussion

Elemental Composition

The results of ICP-OES analysis of 46 samples from Sangtarashan are presented in Table 2. These data reveal that all samples consist of binary tin bronze alloys. Tin concentrations vary between 1.78 and 14.5 wt%. It is noteworthy that other metallic elements such as arsenic and lead do not represent major constituents in any of the samples. In fact, all other elements are detected as minor or trace constituents only.

The metallurgy of tin bronze emerged in the Early Bronze Age (early third millennium BCE) in western Iran (Luristan) and spread slowly across the Iranian Plateau, as observed from evidence of tin bronze metallurgy during the Late Bronze Age (ca. 2000-1500 BCE) and Early Iron Age in many regions of the Iranian Plateau (Pigott, 2004; Pigott, 2011; Helwing, 2013; Oudbashi, 2019a). Many analytical studies of archaeological materials from the third and second millennium BCE from the Iranian Plateau show that, although evidence of tin bronze in Luristan exists from the Early Bronze Age, the main copper-base metallurgical activity in most of the Plateau region concerns copper and arsenical copper production during that period, sometimes alongside tin bronze.

Analysis of several copper-base artefacts dated to the Early and Middle Bronze Age from west of the Iranian Plateau revealed that tin bronze with varying Sn concentrations appeared there. This is observed in artefacts from Early Bronze Age Luristan graveyards

1 such as Kalleh Nisar and Bani Surmeh, Susa dated to period IVa (second half of third
2 millennium BCE) and at Godin Tepe III:6 (ca. 2600–2400 BCE), as well as the Bronze Age
3 graveyard of Deh Dumen, south-western Iran (Frame, 2010; Fleming et al., 2005; Malfoy
4 and Menu, 1987; Oudbashi et al., 2016c). It is worth noting that these tin bronze artefacts
5 occurred alongside arsenical copper artefacts, which were common during the Early and
6 Middle Bronze Age of western and south-western Iran.

7 The earliest evidence of tin bronze in the central Iranian Plateau and southern highlands of
8 Iran emerges at the end of third millennium BCE into the beginning of the second
9 millennium BCE. Earlier examples of tin bronze are very rare in the Early and Middle
10 Bronze Age in central Iran. Nevertheless, a few analysed artefacts from the Bronze Age site
11 Qoli Darvish (middle and late Bronze Age) show that there is no specific system of copper
12 alloying at that time and one low tin bronze artefact illustrates the early use of tin bronze at
13 this site (Nezafati and Stöllner, 2017).

14 Chemical analysis of numerous copper-base artefacts from the Late Bronze Age sites of
15 Tappeh Bazgir and Shahrak-e Firouzeh in north-eastern Iran revealed that apart from a few
16 low-tin bronze artefacts, all of the analysed artefacts were probably made of copper and an
17 arsenical copper alloy (Lorenz, 2008; Oudbashi et al., 2020). The use of tin bronze is
18 observed in south-central Iran during the early second millennium BCE in the Kaftari phase
19 at Malyan (ca. 2200-1800 BCE), and at Tappeh Yahya IVA (Pigott et al., 2003; Thornton et
20 al., 2002). The analytical studies reveal that tin bronze metallurgy rarely occurred during
21 the Bronze Age, and this is especially true in more eastern regions.

22 Analysis of various artefacts and slags from the Bronze Age sites such as Shahdad, Shahr-i
23 Sokhta and Tappeh Hissar gave little to no evidence of tin bronze metallurgy during the
24 third and second millennium BCE in the north-eastern Iran and in the eastern part of the Lut
25 desert, while arsenical copper (or arsenical bronze) was common at these sites during the
26 Bronze Age (Hauptmann et al., 2003; Meier, 2011; Meier, 2015; Pigott et al., 1982;
27 Thornton 2009). Nonetheless, it is worth noting that a limited number of tin-containing
28 copper artefacts (tin bronzes) is observed among the analysed artefacts from Khenaman or
29 Khinaman, a Bronze Age cemetery located in the Lut Desert, which is related to the
30 Shahdad culture (Curtis, 1988; Maxwell-Hyslop, 1988). In summary, these studies show

that tin bronze was the main copper-base alloy for metal artefact production on the Iranian Plateau during the Iron Age, but less so during the Bronze Age (Oudbashi, 2019a; 2019b). Figure 5 presents binary diagrams of main elemental constituents of some Iron Age artefacts from different sites of the Iranian Plateau, in which most artefacts are from the Luristan region, except for Haft Tappeh (south-western Iran), Marlik and Sagzabad (northern Iran) and Hasanlu IVB level (north-western Iran). Background information on the data used for comparison in Figure 5 are presented in Table 3. In Figures 5a and 5b, the scatter plot of Cu versus Sn shows that the majority of the analysed Iron Age artefacts are made of tin bronze and that tin concentrations vary in a wide range in different artefacts from different sites. Figures 5c and 5d present a scatter plot of Sn versus As, the main alloy constituents of prehistoric copper-base artefacts. It is obvious that arsenic did not play an important role in the metallurgy of copper alloys during the Iron Age. Evidence of impure copper and arsenical copper, alongside tin bronze, is found only in some cases, such as Godin Tepe (western Iran), Luristan Bronzes from the Ashmolean museum with no archaeological provenance, Sagzabad and Marlik (northern Iran), Hasanlu (north-eastern Iran) and Haft Tappeh (south-western Iran). Furthermore, the scatter plot presented in Figures 5e and 5f (Sn versus Pb) shows the limited role of lead as an alloying ingredient in the metallurgy of copper alloys during the Iron Age of the Iranian Plateau. Lead has been measured as a major constituent (> 1 wt%) in the composition of a few artefacts from the Ashmolean museum (5 artefacts), Haft Tappeh (4 artefacts), War Kabud (7 artefacts) and Baba Jilan (one artefact) and Hasanlu (5 artefacts) only.

Figure 6 shows scatter plots of trace elements measured in the majority of the artefacts analysed stemming from Iron Age Iran. From the diagram of Ag versus Ni (Figure 6a), it is clear that the Sangtarashan artefacts exhibit a variable and wide range, partially overlapping with the ranges observed for other artefacts from different sites. The largest overlap can be noted with War Kabud, Baba Jilan and the Ashmolean collection (Luristan Bronzes) and partially with Haft Tappeh and Marlik (Iron Age I), as well as Hasanlu. Furthermore, the diagram indicates that some Sangtarashan artefacts differ strongly from others from a trace element perspective. Figure 6b shows a scatter plot of As versus Sb. Here, it is again obvious that the Sangtarashan artefacts encompass a wide range of compositional

variability. However, a linear relationship in the As-Sb ratio is visible in the diagram. The Sangtarashan artefacts partially overlap with many artefacts from different sites, such as Haft Tappeh, Marlik, Baba Jillan, Ashmolean collection, War Kabud, and even with Sagzabad and Hasanlu. It can be derived from both diagrams that, although artefacts from each site/collection overlap with each other to some extent, the Sangtarashan artefacts are strongly variable from a (trace) elemental perspective and overlap with artefacts from most of the different sites/collections. Although this variability is partially visible in artefacts from Marlik and Haft Tappeh as well, it is far more pronounced in the Sangtarashan bronzes, indicating the probable use of various copper sources to manufacture the copper alloy artefacts. In sum, this study of trace elements can be indicative of the possible origin (ore source) of the copper used in the ancient alloys (Pernicka, 2014; Pollard and Bray, 2014), however, in this article we have placed our emphasis on the use lead isotope analysis in an effort to define the provenance of the copper alloy artefacts analysed and presented herein.

Lead Isotopic Analysis

The lead isotope ratios for the Sangtarashan samples, presented in Table 4, vary between 18.051 and 18.904 for $^{206}\text{Pb}/^{204}\text{Pb}$, 15.121 and 15.716 for $^{207}\text{Pb}/^{204}\text{Pb}$, and 37.472 and 39.004 for $^{208}\text{Pb}/^{204}\text{Pb}$. As illustrated in Figure 7, the lead isotope ratios in the Sangtarashan samples follow a linear trend line, apart from three samples which deviate substantially from the trend line in both the $^{206}\text{Pb}/^{204}\text{Pb}$ versus $^{207}\text{Pb}/^{204}\text{Pb}$ and $^{206}\text{Pb}/^{204}\text{Pb}$ versus $^{208}\text{Pb}/^{204}\text{Pb}$ scatter plots (samples ST-06, ST-10 and ST-34).

The lead isotope ratio data available for archaeological objects and metallurgical materials from prehistoric sites in Iran are limited and only some data are available for comparison (see Table 5 for further information). It is worth noting that lead isotope ratios used for comparative studies are from a range of sites across the Iranian Plateau from late Chalcolithic/Bronze Age to Iron Ages. Furthermore, lead isotope ratio data for Iranian ore deposits (ancient and modern) are also limited. Nevertheless, the data available provide a useful comparison to the lead isotope ratios obtained for the Sangtarashan bronzes, as presented in Figure 8. The scatter plots are presented in three formats: full isotopic range

(Figures 8a and 8b), reduced range of archaeological objects (e.g., copper alloy artefacts, slag and matte) (Figures 8c and 8d) and reduced range of ore deposits (Figures 8e and 8f) in comparison with Sangtarashan lead isotope ratio data. Figures 8a and 8b illustrate that, apart from some cases, the lead isotope ratios of the majority of objects and ores are in a similar range and plot along the same trend line. It is noteworthy that the three outliers from Sangtarashan have lead isotope ratios not previously observed for Iranian objects or ore deposits.

Plots of $^{206}\text{Pb}/^{204}\text{Pb}$ versus $^{207}\text{Pb}/^{204}\text{Pb}$ (reduced to a range of 17.8 to 19.4 for $^{206}\text{Pb}/^{204}\text{Pb}$ and of 15.5 to 16 for $^{207}\text{Pb}/^{204}\text{Pb}$, respectively, as presented in Figures 8c and Figure 8e) and $^{208}\text{Pb}/^{204}\text{Pb}$ (reduced to a range of 38 to 39.4, as presented in Figures 8d and 8f), reveal two interesting aspects. First, the majority of samples (both archaeological objects and ores) plot on a broad trend line, and second, the distribution for the Sangtarashan samples is almost as wide as the entire distribution observed for objects from different areas overall, and wider than most individual groups previously characterised. The lead isotope ratios for objects from Arisman (second half of fourth millennium and beginning of third millennium BCE) and sites in the Pusht-i Kuh region equally exhibit a wide range, similar to the Sangtarashan objects. The lead isotope ratios for five samples from Arisman and two samples from the Pusht-i Kuh deviate more strongly from the others of these groups. This is also visible for one sample from Tappeh Sialk. The lead isotope ratios of Sangtarashan artefacts agree well with some of the other data, especially for the Pusht-i Kuh region, the Louvre collection, Qoli Davrish, Tappeh Sarm, Shahr-i Sokhta, etc. However, there is no complete overlap between the data for the Sangtarashan artefacts and those from other archaeological sites, with part of the data being different, for instance, when comparing samples from Arisman, the Pusht-i Kuh and Shahr-i Sokhta.

By comparing lead isotope ratios for ore deposits to those for Sangtarashan artefacts (reduced range), it becomes clear that a significant number of samples from Sangtarashan show relatively poor agreement with the known lead isotope ratios of Iranian copper ores. The western ore deposits in the spread along the Astaneh-Sarband area are the nearest copper sources to Luristan that may have been used in prehistory based on evidence observed from the copper-tin ore deposits at Deh Hosein (Nezafati, 2006). There is a partial

(but limited) overlap between lead isotope ratios for some samples from Sangtarashan and Deh Hosein deposits, as well as with those for copper ore sources from Astaneh. Furthermore, the Sangtarashan lead isotope ratios partially overlap with those for copper ore sources located further away in central Iran, such as ore deposits in Anarak, Karkas and Veshnaveh, Kerman (south-central Iran) and even with eastern ore deposits located in the Lut blocks (Pernicka et al., 2011; Nezafati and Stöllner, 2017; Shafiei, 2010; Hauptmann et al., 2003). However, none of the lead isotope ratio data for these deposits individually follows the trend line observed for the Sangtarashan artefacts. Finally, it is important to highlight that three samples from Sangtarashan have completely different lead isotope ratios, showing no overlap with any data for archaeological objects or ore deposits available to the authors. Comparable published lead isotope ratios are very rare not only for Iranian deposits, but exist for others much further afield (Killick et al., 2020), including a few Cenozoic and Mesozoic lead ores from China (Hsu and Sabatini, 2019) and a Palaeozoic azurite/malachite deposit from Asturias, Spain (Huelga-Suarez et al., 2014). These instances do not represent convincing source areas, and the lead isotope ratios for these three artefacts remain to be explained.

Luristan Bronzes: Technology and Provenance

Copper-base metallurgy during the Iron Age in Luristan (western Iran) can be considered primarily a tin bronze metallurgy, including the manufacture of various ritual artefacts with different shaping methods, such as casting and thermo-mechanical processes. Although this seems to be the commonplace metallurgical process for this time period, some interesting aspects can be highlighted based on the analytical studies presented here and in previous research. One of the important aspects of tin bronze metallurgy in Luristan is that manufacturing artefacts with a binary alloy is the main metallurgical process and other alloying or metallic elements play little or no important role in this technology. In fact, although tin bronze emerged and slowly spread during the Bronze Age, it was selected as the main copper-base alloy by ancient Iranian metalworkers in the Iron Age for producing routine and ritual artefacts. Of course, it is worth noting that (impure) copper and arsenical copper are also observed in some archaeological sites as main metals for producing

artefacts during the Iron Age, such as at Marlik, Haft Tappeh and Sagzabad (Oudbashi and Hessari, 2017; Oudbashi et al., 2019; Oudbashi and Mishmastnehi, 2020; Oudbashi et al., in press; Vatandoost-Haghighi, 1977). However, this is not observed among the Luristan Bronzes. The results of elemental analysis of different collections from the Luristan Bronzes (see Table 3) reveal that among the 164 artefacts belonging to the archaeological sites (War Kabud, Bard-i Bal, Godin Tepe, Sangtarashan and Baba Jilan), as well as museum collections (Ashmolean and Iran National Museum), only 3 artefacts – from the Ashmolean collections – and 5 artefacts from Iron Age of Godin Tepe have low amounts of tin. Furthermore, arsenic has been measured as a major constituent (>1 wt.%) only in a few artefacts from archeological sites, including War Kabud (4 artefacts), Ashmolean collections (4 artefacts), Godin Tepe (6 artefacts), Baba Jilan (2 artefacts), Marlik (4 artefacts), Haft Tappeh (2 artefacts), Sagzabad (one artefacts) and Hasanlu (2 artefacts). Another interesting aspect of tin bronze metallurgy in Luristan is the variable tin content in the artefacts. Based on previously published works, it has been suggested that the prehistoric tin bronze artefacts from the Bronze Age and Iron Age (Iron Age tin bronzes from Luristan) were produced using an uncontrolled (or uncontrollable) alloying process (Oudbashi et al., 2016a; Oudbashi and Hessari, 2017; Oudbashi and Hasanpour, 2018). In literature, different procedures to produce tin bronze alloy in the ancient time have been suggested (Pigott 2004; Rovira et al., 2009; Valério et al., 2013; Murillo-Barroso et al., 2010; Erb-Satullo et al., 2015; Nezafati 2006; Figueiredo et al., 2010; Berger et al., 2019; Farci et al., 2017, Rademakers and Farci 2018; Rademakers et al., 2018):

- co-smelting of copper and tin ores;
- cementation of metallic copper with cassiterite;
- the use of a complex Sn-bearing copper ore for the smelting of copper;
- metal recycling or re-melting of broken metal pieces;
- and direct melting of copper and tin metal together in the crucible.

Apart from the final method that may have allowed ancient metalworkers to control the Cu/Sn ratio precisely in the final products, it may have been relatively difficult for metalworkers to control the tin content in the final product (artefact/ingot). However, the direct alloying of metallic copper and tin appears to have been unlikely in Luristan (see

further below). This is in contrast with the ancient cuneiform texts from Mesopotamia, in which recipes for the constant proportion of Cu/Sn for groups of artefacts from a typological/functional viewpoint are described (Potts 1997; Joannes 1997; Helwing 2009). However, the results of analytical studies on Mesopotamian copper-base artefacts show that proportional control is not commonplace and an uncontrolled alloying process for tin bronze production appears to have been used for the Mesopotamian artefacts during the same period (Hauptmann and Pernicka, 2004). In fact, it can be assumed that the ancient writers may well have referred to the tin oxide (cassiterite) and copper ores (sulphidic or oxidic) instead of metallic copper and tin (Oudbashi and Hasanpour, 2018; Oudbashi et al., 2019).

It is important to note that all artefacts from Sangtarashan analysed are vessels (or vessel accessories such as pins, handles and spouts) and tin concentrations vary among the samples from 1.78 to 14.5 wt%, showing no correlation between tin concentration and artefacts typology. This variability was observed previously in other copper-base artefacts from prehistoric Iran, including Marlik and Deh Dumen (Oudbashi and Hessari, 2017; Oudbashi et al., 2016c), and particularly in vessels from War Kabud and Sangtarashan (Oudbashi, 2019b).

For the artefacts presented in this study, the variability in tin concentrations can be highlighted for vessels from which multiple samples were taken. Examples such as ST.02-10, ST.10-10 and ST.20-10 demonstrate differences in tin concentrations of up to 7 wt%. These differences are accompanied by distinct lead isotope ratios for the different parts, suggesting that these vessels are either composite artefacts, combining different pieces of tin bronze, or some of the pieces analysed may not belong to the same vessel. In contrast, parts from other vessels, such as ST-285, have more homogeneous tin concentrations, despite having distinct lead isotope ratios. Finally, some vessels illustrate the use of the same bronze composition for different parts of the vessel. For example, the same metal batch was used for the vessel body and one shield pin in ST-KH, while another shield pin from the same vessel was made from a distinct tin bronze: this may indicate the flexible use of different raw materials in the manufacture of a single vessel and/or its repair over time. Similarly, lead isotope ratios for the vessel body and edge fragments from ST.04-10 and

1 ST.08-10 are indistinguishable, although minor variations in tin concentrations can be
2 noted.

3 Furthermore, the elemental analysis of the artefacts of Sangtarashan presents a wide range
4 of compositional properties with apparent similarities with different groups of artefacts
5 from other archaeological sites. In fact, the majority of Sangtarashan bronzes are similar to
6 artefacts from Luristan (such as War Kabud and unprovenanced artefacts), while some
7 samples are comparable to artefacts from non-Luristan sites such as Sagzabad or Marlik in
8 northern Iran, from an elemental composition viewpoint (see Figure 6).

9 Accordingly, it can be suggested from the available alloy composition data for Luristan (as
10 well as other Iron Age sites in Iran) that Luristan metalworkers did not systematically
11 control tin concentrations in the final products: they may not have been able to do so given
12 the raw materials and technological knowledge available to them, or were not interested in
13 doing so, possibly due, in part, to the ritual function of the Luristan Bronzes. Adding less
14 than about 15 wt% tin to copper to make binary alloy leads to a material with physical
15 properties, colour, in particular, that are not strongly but partially influenced by the tin
16 concentration, although the change in these properties increases at higher tin
17 concentrations, as in the decorative artefacts manufactured from high-tin bronzes (Scott
18 2010; Meeks 1993a; Meeks 1993b). However, it is possible that the Luristan craftspeople
19 may have varied the tin concentrations intentionally to obtain a variety of properties, such
20 as some variable colour and workability, which may have been of technical, as well as of
21 ritual interest (e.g., Mödlinger et al., 2017; Radivojević et al., 2018). Consequently, the
22 Luristan metalworkers didn't systematically control the alloying process which lead to the
23 production of tin bronze artefacts with variable tin contents, perhaps because it was not
24 possible to do so or perhaps because such a treatment was of lesser importance to them.

25 With regard to the lead isotope ratio distribution of the Sangtarashan artefacts, the data for
26 nearly all samples fall along a wide trend line, and only three samples show divergent lead
27 isotope ratios (samples ST-06, ST-10 and ST-34). These are the edge of artefacts ST.03-10,
28 the vessel base from artefacts ST.06-10 and the body of a large handled kettle (sample
29 ST.22-11), respectively. Interestingly, the elemental composition of these three samples
30 doesn't appear distinct from the other Sangtarashan artefacts. The wide distribution of

1 Sangtarashan lead isotope ratios is most likely indicative of the use of different copper ore
2 deposits to obtain copper metal. The comparative analysis of the lead isotope ratios also
3 indicates similarity with numerous artefacts and ore deposits from different regions on the
4 Iranian Plateau.

5 Comparison with lead isotope data from Bronze and Iron Age objects from different
6 locations from Iran revealed that some Sangtarashan artefacts are consistent with artefacts
7 from western Iran (Luristan in particular), while strong similarity is observed as well with
8 some objects from archaeological sites located further away in central and eastern Iran,
9 such as Tappeh Sialk, Arisman, Tappeh Sarm and Qoli Darvish, and even further away at
10 Shahr-i Sokhta.

11 The lead isotope ratios of several ore deposits from different regions of Iran are partially
12 consistent with those of the Sangtarashan bronzes. In fact, it is not possible to attribute the
13 Sangtarashan artefacts to one or more specific ore deposits from a lead isotope ratio
14 perspective. However, some artefacts of the collection analysed are consistent with ore
15 deposits close to the Luristan region and located in the Astaneh-Sarband area (e.g., Deh
16 Hosein and Astaneh), while some other samples are consistent with lead isotope ratios of
17 ore deposits that are located further away from the Luristan region in central Iran (Karkas
18 and Veshnavah), as well as in the Anarak region on the central Iranian Plateau (Pernicka et
19 al., 2011; Nezafati and Stöllner, 2017; Shafiei, 2010; Hauptmann et al., 2003). Some are
20 even weakly consistent with ore deposits located very far away in the eastern part of the
21 Plateau located in the Lut block. It is worth noting that the ore deposits used for comparison
22 include both sulphidic and oxidic copper ores (see Table 5). While a partial overlap exists
23 between these different ore deposits and the Sangtarashan artefacts in terms of lead isotope
24 ratios, insufficient trace element data is available to validate them further as possible source
25 candidates. An interesting matter is the presence of tin ores (cassiterite) and high tin
26 concentrations in copper ores of the Astaneh-Sarband area (Deh Hosein and Nezam Abad),
27 which has been identified as a potential source area for direct production of tin bronze
28 during prehistoric times in Iran (Nezafati, 2006).
29 During the last decade, the Astaneh-Sarband area (Sanandaj-Sirjan metamorphic belt), and
30 in particular its Deh Hosein ancient copper mines, have been introduced as a potential ore

deposit used for tin bronze production in the Bronze Age and Iron Age of Luristan, presumably during the second and first millennium BCE (Nezafati, 2006: 2, Fig. 1.1; Nezafati et al., 2006). The ancient mining sites at Deh Hosein are located about 45 km from Arak city, the eastern part of central Zagros on the north-eastern border of ancient Luristan. Numerous ellipsoidal open depressions from ancient mining activities have been documented, distributed over an area of 27 km². Analytical studies suggest that it may have been in use from the 3rd millennium BCE onwards as a major supplier of tin (bronze) for Iran and Mesopotamia, as well as regions further west (Nezafati et al., 2006; Nezafati et al., 2011). It is worth noting that ancient cuneiform texts mention “tin from the East” of Mesopotamia, that may possibly be matched with the Deh Hosein mines (Muhly, 1973; Moorey, 1994; Pigott 2011: 284-285; Weeks, 1999; 2004). Its proximity to Luristan and the presence of complex copper-tin ores at Deh Hosein, as well as the matching lead isotope ratios of some (especially Bronze Age) Luristan artefacts with those of Deh Hosein ores, have argued for it as one of the main known copper-tin ore deposits used in prehistoric times on the Iranian Plateau. The specific elemental composition of the (Cu-Sn-W-Au) Deh Hosein ores presents the possibility that the direct smelting of complex copper-tin ores was an important alloying method for tin bronze production from Deh Hosein ores (Momenzadeh, 2004; Nezafati, 2006; Pigott 2021). However, Deh Hosein has yet to yield any evidence of prehistoric copper smelting activity. Nevertheless, the lead isotope ratios of tin bronze artefacts from Sangtarashan presented here revealed only a partial overlap with those of the Astaneh-Nezam Abad area (especially Deh Hosein), while the lead isotope ratio data for a significant number of the Sangtarashan artefacts show little consistency with the signature of the ore deposits in this area. It may be suggested, therefore, that the Astaneh-Sarband ore deposits may have been used during the Iron Age as a resource for tin bronze production in Luristan, but not exclusively.

The elemental and lead isotopic analyses of the Sangtarashan bronzes show that it is not possible to identify one specific ore deposit or region as the source of copper for tin bronze metallurgy in the Iron Age of Luristan. No evidence of smelting or metal working has been discovered in Luristan yet and it is not clear as yet where the Luristan Bronzes were produced. From an archaeological perspective, the Luristan Bronzes show a specific artistic

style, but the analytical data show that they were most likely produced from a variety of ore sources, and possibly in different workshops. Accordingly, the following hypotheses can be suggested:

1. The Luristan Bronzes are ritual/funerary artefacts that have been produced in different regions using local ore deposits and were exported from / transported to Luristan to be placed in graves or sanctuaries.
2. The copper (and tin) ores have been imported from different regions of the Iranian Plateau (or even elsewhere) and smelted in the local workshops in Luristan and then the ingots in copper and tin were used to manufacture the Luristan Bronzes.
3. The metallic raw materials (possibly including tin bronze ingots) were produced elsewhere and then brought to Luristan to produce artefacts in the Luristan style.

The first is less likely because of the unique and homogeneous artistic style of the Luristan Bronzes, and it is difficult to imagine the production of highly similar artefacts in different regions on the Plateau or further afield. However, no local smelting and/or metal working workshops have there been located in Luristan yet, although it is possible that future archaeological and field studies may yield new evidence in this regard. The lack of (hitherto known) local metallurgical activity has been ascribed to the difficult topography of the Luristan region (with high mountains and deep valleys), possibly hindering the establishment of large-scale production during prehistory (Begemann et al., 2008; Moorey, 1969). Nevertheless, the results of the analytical studies show that the Luristan Bronzes technology cannot be interpreted as an entirely local industry, as the raw materials used (or, less probably, the final artefacts) have been imported from different regions of Iran. In fact, this region was very important (or sacred) during the Iron Age and people from different regions may have presented these artefacts as gifts in the graves/sanctuaries. It is possible that these artefacts were transported by ancient nomadic peoples that may have been responsible for the formation of Luristan culture during the Iron Age. These artefacts could have been manufactured by them elsewhere and then aggregated in the sacred places in Luristan. This is already an old hypothesis developed by archaeologists as early as the last century due to absence of Iron Age settlement evidence in Luristan (e.g., Godard 1931; see

also Overlaet, 2004; Porada, 1964). Recent excavation evidence, however, argues against this hypothesis.

Based on currently available evidence, it is thus most likely that raw metals, copper and tin, were brought to Luristan for the production of these vessels. Apart from copper, tin and/or tin bronze ingots, the possibility of recycled bronze from different regions in Iran being used for the production of these bronzes in Luristan could equally fit the picture painted by the new data presented here.

A notable possibility is that tin may have been imported to Luristan from the southern lowlands. The Elamite civilization was located in southern and south-eastern Luristan and provided a trade route between the Mesopotamian lowlands and the Iranian Plateau during third to first millennium BCE. One avenue of further research is the potential interaction of Elam with Luristan as arguments have been made for the potential control of the tin trade ‘from the East’ by the Elamites (Pigott, 2021; Helwing, 2009).

Overall, these data suggest that the Luristan Bronzes found at Sangtarashan were produced following a variety of tin bronze recipes and a wide range of raw materials. The variability in alloy compositions may be a reflection of these different raw materials (including bronze ingots) arriving in Luristan and being used to produce the artefacts, without any systematic selection by the Luristan metalworkers. Variability between different workshops may have existed as well. To elucidate this further, future study of production remains will be essential. Regardless, the results presented here shed a new light on the provisioning systems underlying the Luristan Bronzes, which were of key importance in the technology, religion and trade underway on the Iranian Plateau during the Iron Age.

Conclusion

This paper has presented the results of an extensive archaeometallurgical study on Luristan Bronzes dating back to the first millennium BCE and excavated from the Sangtarashan sanctuary located in the Pish-i Kuh region of Luristan (western Iran). This study aimed to investigate the alloying technologies and provenance of the raw materials used, based on elemental and lead isotopic analysis of a series of copper-base artefacts from the site along with a broad-based comparison with available data from previous studies on copper-base

1 artefacts and copper ore deposits from the Iranian Plateau. The results of elemental analysis
2 showed that the Sangtarashan artefacts are made of tin bronze alloys with variable tin
3 concentrations, while other metallic constituents are only visible as impurities in the
4 composition of these artefacts. Such variation in the tin content has been observed
5 repeatedly for prehistoric tin bronze artefacts of Iran from the third to first millennia BCE.
6 Other materials such as arsenical copper and impure copper were used during the Bronze
7 Age and Iron Age in some regions of Iran as well, although during the Iron Age (ca. 1500-
8 550 BCE). tin bronze was the main copper-base technology. The provenance studies on the
9 Sangtarashan tin bronze artefacts have shown that this collection -as well as other artefacts
10 attributed to the Luristan Bronzes- may not have been produced by using a specific ore
11 deposit and it is more probable that these artefacts have been produced from different
12 copper (ore) sources from widespread ore deposits across Iran (and presumably
13 neighbouring regions). This production may have relied on the import of ores from
14 different regions or, more likely, the trading of raw metals (including copper and tin ores,
15 but possibly also tin bronze ingots and recycled tin bronzes) from other regions to Luristan
16 to manufacture the individual artefacts by Luristan metalworkers. The variability in alloy
17 compositions for similar artefacts (for example the Sangtarashan vessels) may be a
18 reflection of using different raw materials (including copper and tin ores) arriving in
19 Luristan to produce these artefacts, or perhaps the weak control of tin concentrations during
20 the alloying process by the Luristan metalworkers. It is worth noting that it is not possible
21 to specify one or more places as metallurgical workshops for manufacturing the Luristan
22 Bronzes due to a lack of archaeological data on this subject, but it is quite possible that they
23 have been manufactured by peoples who lived in Luristan, including perhaps ancient
24 nomads who migrated to Luristan during the Iron Age, using ores and raw materials from
25 different regions. Given the importance of the Elamite empire (not civilization) and its
26 widespread influence in south-western Iran and beyond, tin in particular may have reached
27 Luristan via Elam as the empire lies immediately to the south and appears to have been
28 actively involved in the tin trade. Finally, the present study clarified more details about the
29 technology and provenance of the Luristan Bronzes, especially by showing the use of
30 widespread copper sources on the Plateau apparently used to produce these the

1 Sangtarashan and other related Luristan Bronzes. Nevertheless, it is necessary to expand
2 archaeometallurgical and archaeological research on the Luristan Bronzes to obtain a
3 clearer picture of their copper-base metallurgy during the prehistoric period of western Iran.
4

5 **Acknowledgements**

6 We are grateful to Kris Latruwe for performing quantitative Pb determination using ICP-
7 MS and Pb isotopic analysis using MC-ICP-MS at Ghent University, and Elvira Vassilieva
8 for chemical analyses performed at KU Leuven. This research was funded by the KU
9 Leuven Centre for Archaeological Sciences (CAS). We are also thankful to Prof. Vincent
10 C. Pigott from University of Pennsylvania for reading the manuscript and providing useful
11 scientific comments and corrections on the paper. The Flemish Research Foundation
12 (FWO) is also acknowledged for providing the funding for the acquisition of the MC-ICP-
13 MS instrumentation (ZW15-02 – G0H6216N). Also we are tankful from Deputy of
14 Research and Technology of Art University of Isfahan and Iranian Center for
15 Archaeological Research (ICAR) for support this research project. We are very grateful to
16 the two anonymous reviewers for their very constructive feedback which has helped to
17 improve this manuscript.
18

19 **References**

- 20 Begemann, F., Haerinck, E., Overlaet, B., Schmitt-Strecker, S., Tallon, F., 2008. An
21 Archaeo-Metallurgical Study of the Early and Middle Bronze Age in Luristan, Iran. Iran.
22 Antiq. XLIII, 2-66.
- 23 Berger, D., Brugmann, G., Pernicka, E., 2019. On Smelting Cassiterite in Geological and
24 Archaeological Samples: Preparation and Implications for Provenance Studies on Metal
25 Artefacts with Tin Isotopes. Archaeol. Anthropol. Sci. 11, 293-319.
- 26 Calmeyer, P., 1969. Datierbare Bronzen aus Luristan und Kirmanshah, de Gruyter, Berlin.
- 27 Chegini, N.N., Momenzadeh, M., Parzinger, H., Pernicka, E., Stöllner, T., Vatandoust, R.,
28 Weisgerber, G., 2000. Preliminary Report on Archaeometallurgical Investigations around
29 Prehistoric Site of Arisman Near Kashan, Western Central Iran. Archäologische
30 Mitteilungen aus Iran und Turan 32, 281-318.

- 1 Curtis, J., 1988. A Reconsideration of the Cemetery at Khinaman, Southeast Iran. Iran.
2 Antiq. XXIII, 97-124.
- 3 De Muynck, D., Cloquet, C., Vanhaecke, F., 2008. Development of a New Method for Pb
4 Isotopic Analysis of Archaeological Artefacts using Single-Collector ICP-Dynamic
5 Reaction Cell-MS. J. Anal. Ato. Spectrom. 23, 62-71.
- 6 Erb-Satullo, N.L., Gilmour B.J.J., Khakhutaishvili, N., 2015. Crucible Technologies in the
7 Late Bronze Early Iron Age South Caucasus: Copper Processing, Tin Bronze Production,
8 and the Possibility of Local Tin Ores. J. Archaeol. Sci. 61, 260-276.
- 9 Farci, C., Martinon-Torres, M., Gonzalez Alvarez, D., 2017. Bronze Production in the Iron
10 Age of the Iberian Peninsula: The Case of El Castro, Vigana (Asturias, NW Spain). J.
11 Archaeol. Sci. Rep. 11, 338-351.
- 12 Figueiredo, E., Silva, R.J.C., Senna-Martinez, S.C., Araujo, M.F., Fernandes, F.M.B., Ines
13 Vaz, J.L., 2010. Smelting and recycling evidences from the Late Bronze age habitat site of
14 Baioes (Viseu, Portugal). J. Archaeol. Sci. 37, 1623-1634.
- 15 Fleming, S.J., Nash S.K., Swann, C.P., 2011. The Archaeometallurgy of the Period IVB
16 Bronzes at Hasanlu, in: Maude de Schauensee (Ed.), Peoples and Crafts in Period IVB at
17 Hasanlu, Iran, University of Pennsylvania Museum of Archaeology and Anthropology,
18 Philadelphia, pp. 102-134.
- 19 Fleming, S.J., Pigott, V.C., Swann, C.P., Nash, S.K., Haerinck, E., Overlaet, B., 2006. The
20 Archaeometallurgy of War Kabud, Western Iran. Iran. Antiq. XLI, 31-57.
- 21 Fleming, S.J., Pigott, V.C., Swann, C.P., Nash, S.K., 2005. Bronze in Luristan: Preliminary
22 Analytical Evidence from Copper/Bronze Artifacts Excavated by the Belgian Mission in
23 Iran. Iran. Antiq. XL, 35-64.
- 24 Frame, L.D., 2010. Metallurgical Investigations at Godin Tepe, Iran, Part I: The Metal
25 Finds. J. Archaeol. Sci. 37, 1700-1715.
- 26 Galer, S.J.G., Abouchami, W., 1998. Practical Application of Lead Triple Spiking for
27 Correction of Instrument Mass Discrimination. Mineral. Mag. 62, 491-492.
- 28 Godard, A., 1931. Les Bronzes du Luristan, Les Editions G. Van Oest, Paris.

- 1 Goff, C., 1968. Luristan in the First Half of the First Millennium BC., a Preliminary Report
- 2 on the First Season's Excavations at Baba Jan, and Associated Surveys in the Eastern Pish-i
- 3 Kuh. Iran 6, 105-134.
- 4 Haerinck, E., 2009. Louis Vanden Berghe, Encyclopaedia Iranica Online, Originally
- 5 Published: July 20, 2009, <https://iranicaonline.org/articles/vanden-berghe-louis>
- 6 Haerinck, E., Overlaet, B., Jaffar-Mohammadi, Z., 2004. Finds from Khatunban B –
- 7 Badavar Valley (Luristan) in the Iran Bastan Museum. Iran. Antiq. 39, 105-168.
- 8 Haerinck, E., Overlaet, B., 2004a. The Chronology of the Pusht-i Kuh, Luristan, Results of
- 9 the Belgian Archaeological Mission in Iran, in: From Handaxe to Khan, Essays Presented
- 10 to Peder Mortensen on the Occasion of his 70th Birthday, Aarhus, 119-135.
- 11 Haerinck, E., Overlaet, B., 2004b. The Iron Age III Graveyard at War Kabud, Pusht-i Kuh,
- 12 Luristan, Luristan excavation documents 5, Acta Iranica 42, Leuven.
- 13 Haerinck, E., Overlaet, B., 1999. Djub-i Gauhar and Gul Khanan Murdah: Iron Age III
- 14 Graveyards in the Aivan Plain, Luristan excavation documents 3, Acta Iranica 36, Leuven.
- 15 Haerinck, E., Overlaet, B., 1998. Chamahzi Mumah: An Iron Age III Graveyard, Luristan
- 16 excavation documents 2, Acta Iranica 33, Leuven.
- 17 Hasanpur, A., Malekzadeh, M., 2019. Sangtarashan after Six Seasons of Archaeological
- 18 Excavations, in: Hassanzadeh, Y., Vahdati, A.A., Karimi, Z. (Eds.), Proceedings of the
- 19 International Conference on the Iron Age in Western Iran and Neighbouring Regions, Vol.
- 20 1, RICHT, National Museum of Iran and Kurdistan ICHHTO Publications, Tehran, pp.
- 21 151-174 (in Persian).
- 22 Hasanpur, A., Hashemi, Z., Overlaet, B., 2015. The Baba Jilan Graveyard near Nurabad,
- 23 Pish-i Kuh, Luristan. Iran. Antiq. 50, 171-212.
- 24 Hashemi, Z. Malekzadeh, M., Hasanpour, A., 2021. Sangtarashan: un Lieu Rituel à l'âge du
- 25 Fer au Pish Kuh du Luristan, Luristan Excavation Documents, Acta Iranica, Peeters,
- 26 Leuven.
- 27 Hauptmann, H., Pernicka, E., (Eds.) 2004. Die Metallindustrie Mesopotamiens von den
- 28 Anfängen bis zum 2. Jahrtausend v. Chr. Orient - Archäologie Band 3. Marie Leidorf,
- 29 Rahden.

1 Hauptmann, A., Rehren, T., Schmitt-Strecker, S., 2003. Early Bronze Age Copper
 2 Metallurgy at Shahr-i Sokhta (Iran), Reconsidered, in: Stöllner, T., Körlin, G., Steffens, G.,
 3 Cierny, J., (Eds.), *Man and Mining—Mensch und Bergbau. Der Anschnitt, Beiheft, Vol 16.*
 4 *Deutsches Bergbau-Museum, Bochum*, pp. 197-213.
 5 Helwing, B., 2013. Early Metallurgy in Iran—an Innovative Region as Seen from the
 6 Inside, in: Burmeister, S., Hansen, S., Kunst, M., Müller- Scheeßel, N., (Eds), *Metal*
 7 *Matters: Innovative Technologies and Social Change in Prehistory and Antiquity,*
 8 *Menschen-Kulturen-Traditionen, Forschungs cluster 2, band 12. Deutsches*
 9 *Archäologisches Institut, Berlin*, pp. 105-136.
 10 Helwing, B., 2009. Rethinking the Tin Mountains: Patterns of Usage and Circulation of Tin
 11 in Greater Iran from the 4th to the 1st millennium BC. *TUBA-AR* 12, 209-221.
 12 Hsu, Y.-K., Sabatini, B.J., 2019. A Geochemical Characterization of Lead Ores in China:
 13 An Isotope Database for Provenancing Archaeological Materials. *PLOS One* 14, e0215973.
 14 Huelga-Suarez, G., Moldovan, M., Suárez Fernández, M., Ángel de Blas Cortina, M.,
 15 García Alonso, J.I., 2014. Defining the Lead Isotopic Fingerprint of Copper Ores from
 16 North-West Spain: The El Milagro Mine (Asturias). *Archaeometry* 56, 88-101.
 17 Joannes, F., 1997. Metalle und Metallurgie, A. I. in *Mesopotamien. Reallexikon der*
 18 *Assyriologie und vorderasiatischen Archäologie* 8, 96-112.
 19 Killick, D., Stephens, J., Fenn, T.R., 2020. Geological Constraints on the Use of Lead
 20 Isotopes for Provenance in Archaeometallurgy. *Archaeometry* 62, 86-105.
 21 Lorenz, S., 2008. Archäometrische untersuchungen am hortfund von Bazgir, Iran,
 22 Diplomarbeit-Magister, Institut für Archäometries, Fakultät für Werkstoffwissenschaft und
 23 Werkstofftechnologie, TU Bergakademie Freiberg (Unpublished).
 24 Malekzadeh, M., Hasanpur, A., Hashemi, Z., 2018. Bronzes of Luristan in a Non-funerary
 25 Context: Sangtarashan, an Iron Age Site in Luristan (Iran), in: Horejs, B., Schwall, C.,
 26 Müller, V., Luciani, M., Ritter, M., Giudetti, M., Salisbury, R.B., Höflmayer, F., Bürge, T.,
 27 (Eds.), *Proceedings of the 10th International Congress on the Archaeology of the Ancient*
 28 *Near East, Vol. 2, Harrassowitz Verlag, Wiesbaden*, pp. 577-588.
 29 Malekzadeh, M., Hasanpur, A., Hashemi, Z., 2017. Fouilles (2005-2006) à Sangtarashan,
 30 Luristan, Iran". *Iran. Antiq.* 52, 61-158.

- 1 Malfoy, J.M., Menu, M., 1987. La Métallurgie du Cuivre à Suse aux IV^e et III^e
2 Millénaires: Analyses en Laboratoire, in: F. Tallon, J.-M. Malfoy (Eds.), Métallurgie
3 Susienne I: 1. De la fondation de Suse au XVIII^e avant J.-C, Paris: Notes et documents des
4 musées de France, Paris.
- 5 Maxwell-Hyslop, K.R., 1988. A Comment on the Finds from Khinaman. Iran. Antiq.
6 XXIII, 129-138.
- 7 Meeks, N., 1993a. Patination Phenomenon on Roman and Chinese High-Tin Bronze
8 Mirrors and Other Artefacts, in: La Niece, S., Craddock, P., (Eds.), Metal Plating and
9 Patination, Cultural, Technical and Historical Developments, Butterworth-Heinemann,
10 Oxford, 63-84.
- 11 Meeks, N., 1993b. Surface Characterization of Tinned Bronze, High-Tin bronze, Tinned
12 Iron and Arsenical Bronze. in: La Niece, S., Craddock, P., (Eds.), Metal Plating and
13 Patination, Cultural, Technical and Historical Developments, Butterworth-Heinemann,
14 Oxford, 247-275.
- 15 Meier, D.M.P., 2015. Traces of protohistorical metallurgical activities during the 3rd
16 millennium BCE in East Iran with a special focus on the case of Shahdad in the Dasht-eh
17 Lut (Kerman province). PhD Dissertation, Freie Universität Berlin.
- 18 Meier, D.M.P., 2011. Preliminary Archaeometallurgical Investigations of Bronze Age
19 Metal Finds from Shahdad and Tepe Yahya. Iranian Journal of Archaeological Studies 1,
20 25-34.
- 21 Momenzadeh, M., 2004. Metallic Mineral Resources of Iran, Mined in Ancient Times: a
22 Brief Review, in: Stöllner, T., Slotta, R., Vatandoust, A., (Eds.), Persia's ancient splendour,
23 mining, handicraft and archaeology. Deutsches Bergbau-Museum, Bochum, pp. 8-21.
- 24 Moorey, P.R.S., 1994. Ancient Mesopotamian Materials and Industries, The
25 Archaeological Evidence, Clarendon Press, Oxford.
- 26 Moorey, P.R.S., 1969. Prehistoric Copper and Bronze Metallurgy in Western Iran (With
27 Special Reference to Lūristān), Iran 7, 131-153.
- 28 Moorey, P.R.S., 1964. An Interim Report on Some Analyses of "Luristan Bronzes".
29 Archaeometry 7, 72-79.

- 1 Mortazavi, M., Salehi Kkakhki, A., Colozar, M.A., Tala'i, H., 2011. Preliminary
2 Metallurgical Investigation of Copper-Based Artifacts at Tepe Sagzabad in Qazvin Plain,
3 Iran (1500-800 BC). *Iranian Journal of Archaeological Studies* 1, 49-59.
- 4 Muhly, J.D., 1973. Copper and Tin, The Distribution of Mineral Resources and the Nature
5 of the Metals Trade in the Bronze Age, The Connecticut Academy of Arts and Sciences,
6 New Haven, Connecticut, pp. 155-536.
- 7 Murillo-Barroso, M., Pryce, T.O., Bellina, B., Martínón-Torres, M., 2010. Khao Sam Kaeo-
8 an Archaeometallurgical Crossroads for Trans-Asiatic Technological Traditions. *J.*
9 *Archaeol. Sci.* 37, 1761-1772.
- 10 Muscarella, O.W., 1990. Bronzes of Luristan, in: Yarshater, E., (Ed.), *Encyclopedia*
11 *Iranica*, Vol. IV, Fasc. 5, pp. 478-483.
- 12 Muscarella, O.W., 1988a. Bronze and Iron: Ancient Near Eastern Artifacts in the
13 Metropolitan Museum of Art, Metropolitan Museum of Art, New York.
- 14 Muscarella, O.W., 1988b. The Background to the Luristan Bronzes, in: Curtis, J.,
15 (Ed.), *Bronzeworking Centres of Western Asia 1000-539 B.C.*, London, pp. 177-192.
- 16 Mödinger, M., Kuijpers, M.H.G., Braekmans, D., Berger, D., 2017. Quantitative
17 Comparisons of the Color of CuAs, CuSn, CuNi, and CuSb Alloys. *J. Archaeol. Sci.* 88,
18 14-23.
- 19 Nezafati, N., 2006. Au-Sn-W-Cu-Mineralization in the Astaneh-Sarband Area, West
20 Central Iran, Including a Comparison of the Ores with Ancient Bronze Artifacts from
21 Western Asia, PhD Thesis, Der Eberhard-Karls-Universität Tübingen.
- 22 Nezafati, N., Stöllner, T., 2017. Economic Geology, Mining Archaeological and
23 Archaeometric Investigations at the Veshnavah Ancient Copper Mine, Central Iran. *Metalla*
24 23, 67-90.
- 25 Nezafati, N., Pernicka, E., Momenzadeh, M., 2011. Early Tin-Copper Ore from Iran, a
26 Possible Clue for the Enigma of Bronze Age Tin. *Anatolian Metal V*, *Der Anschnitt* 24,
27 211-230.
- 28 Nezafati, N., Pernicka, E., Malek Shahmirzadi, S., 2008. Evidence on the ancient mining
29 and metallurgy at Tappeh Sialk (central Iran), in: Yalçın, Ü., Özbal, H., Paşamehmetoğlu,

- 1 A.G., (Eds.), Ancient Mining in Turkey and the Eastern Mediterranean, Atilim University,
2 Ankara, pp. 329-350.
- 3 Nezafati, N., Pernicka, E., Momenzadeh, M., 2006. Ancient Tin: Old Question and a New
4 Answer. *Antiquity* 80, 308
- 5 Oudbashi, O., 2019a. The Bronze Metallurgy in the Iron Age: Tin Bronze Production
6 Tradition during the Iron Age in the Central Zagros, in: Hassanzadeh, Y., Vahdati, A.A.,
7 Karimi, Z. (Eds.), Proceedings of the International Conference on the Iron Age in Western
8 Iran and Neighbouring Regions, Vol. 1, RICHT, National Museum of Iran and Kurdistan
9 ICHHTO Publications, Tehran, pp. 206-219 (in Persian).
- 10 Oudbashi, O., 2019b. A New Look at an Old Technology: Insights into the Metallurgy of
11 Tin Bronze during the Iron Age of Luristan, in: Baas, P., (Ed.), Proceedings of the XXth
12 International Congress on Ancient Bronzes: Resource, Reconstruction, Representation,
13 Role, Bar Publishing, pp. 91-100.
- 14 Oudbashi, O., 2018. A Methodological Approach to Estimate Soil Corrosivity for
15 Archaeological Copper Alloy Artefacts. *Herit. Sci.* 6, 2.
- 16 Oudbashi, O., Mehofer, M., Bahadori, S., Aliyari, A., Tala'i, H., (in press), The Emergence
17 and Spread of Tin Bronze Alloying in Prehistoric Iran – The LBA Metallurgy in Sagzabad,
18 Northern Iran, in: Proceeding of International Conference Archaeometallurgy in Europe
19 (AIE2019).
- 20 Oudbashi, O., Mehofer, M., Basafa, H., Tayyari, J., Bahadori, S., 2020. Arsenical Copper
21 and Bronze Metallurgy during Late Bronze Age of North-Eastern Iran: Evidences from
22 Shahrak-e Firouzeh Archaeological Site. *Archaeol. Anthropol. Sci.* 12, 231.
- 23 Oudbashi, O., Mishmastnehi, M., 2020. Archaeometallurgy of Copper in the Middle
24 Elamite Period of Southwestern Iran: Analytical Investigation of various Parts of the
25 Copper Production in Haft Tappeh. *J. Archaeol. Sci. Rep.* 30, 102216.
- 26 Oudbashi, O., Agha-Aligol, D., Mishmastnehi, M., Barnoos, V., 2019. The Elamite
27 Metalworkers: Multianalytical Study on Copper Objects and Ingots from Second
28 Millennium BC of Southwestern Iran. *Archaeol. Anthropol. Sci.* 11, 2059-2072.

- 1 Oudbashi, O., Hasanpour, A., 2018. Bronze Alloy Production during the Iron Age of
- 2 Luristan: a Multianalytical Study on Recently Discovered Bronze Objects. *Archaeol.*
- 3 *Anthropol. Sci.* 10, 1443-1458.
- 4 Oudbashi, O., Hessari, M., 2017. Iron Age Tin Bronze Metallurgy at Marlik, Northern Iran:
- 5 an Analytical Investigation. *Archaeol. Anthropol. Sci.* 9, 233-249.
- 6 Oudbashi, O., Hasanpour, A., Malekzadeh, M., 2016a. The Luristan Bronzes in
- 7 Sangtarashan: Bronze Technology in Western Iran in the First Millennium BC, in: Giumlia-
- 8 Mair, A., Mattusch, C. C., (Eds.), *Proceedings of the XVIIth International Congress on*
- 9 *Ancient Bronzes*, Izmir, Autun, Éditions Mergoil, pp. 17-27.
- 10 Oudbashi, O., Hasanpour, A., Davami, P., 2016b. Investigation on Corrosion Stratigraphy
- 11 and Morphology in some Iron Age Bronze Alloys Vessels by OM, XRD and SEM-EDS
- 12 Methods, *Appl. Phys. A-Matter.* 122, 262.
- 13 Oudbashi, O., Naseri, R., Malekzadeh, M., 2016c. Technical Studies on the Bronze Age
- 14 Metal Artefacts from the Graveyard of Deh Dumen, South-Western Iran (Third Millennium
- 15 BC). *Archaeometry* 58, 947-965.
- 16 Oudbashi, O., Davami, P., 2014. Metallography and Microstructure Interpretation of some
- 17 Archaeological Tin Bronze Vessels from Iran. *Mater. Charact.* 97, 74-82.
- 18 Oudbashi, O., Emami, S. M., Malekzadeh, M., Hasanpour A., Davami, P., 2013.
- 19 Archaeometallurgical Studies on the Bronze Vessels from Sangtarashan, Luristan, W-Iran.
- 20 *Iran. Antiq.* XLVIII, 147-171.
- 21 Overlaet, B., 2011. Čale Ğār (Kāšān Area) and Votives, Favissae and Cave Deposits in pre-
- 22 Islamic and Islamic Traditions, *Archäologische Mitteilungen aus Iran und Turan* 43: 113-
- 23 140.
- 24 Overlaet, B., 2006. Luristan Bronzes I: The Field Research, in: Yarshater, E., (Ed.)
- 25 *Encyclopaedia Iranica Online*.
- 26 Overlaet, B., 2005. The Chronology of the Iron Age in the Pusht-iKuh, Luristan. *Iran.*
- 27 *Antiq.* XL, 1-33.
- 28 Overlaet, B., 2004. Luristan Metalwork in the Iron Age, Stöllner, T., Slotta, R., Vatandoust,
- 29 A., (Eds.), *Persia's ancient splendour, mining, handicraft and archaeology*. Deutsches
- 30 *Bergbau-Museum, Bochum*, pp. 328-338.

1 Pernicka, E., 2014. Provenance Determination of Archaeological Metal Objects, in: Roberts
2 B.W., Thornton, C.P., (Eds.), *Archaeometallurgy in Global Perspective, Methods and*
3 *Syntheses*, Springer, New York, pp. 239-268.

4 Pernicka, E., Adam, K., Böhme, M., Hezarkhani, Z., Nezafati, N., Schreiner, M.,
5 Winterholler, B., Momenzadeh, M., Vatandoust, A., 2011. *Archaeometallurgical*
6 *Researches at Arisman in Central Iran*, in: Vatandoust, A., Parzinger, H., Helwing, B.,
7 (Eds.), *Early Mining and Metallurgy on the Central Iranian Plateau, Report on the First*
8 *Five Years of Research of the Joint Iranian-German Research Project*, *Archäologische*
9 *Mitteilungen aus Iran und Turan* 9, Philipp von Zabern, Mainz, pp. 633-705.

10 Pigott, V.C., 2021. The Acquisition of Tin in Bronze Age Southwest Asia. in: Lyonnet, B.,
11 Dubova, N.A., (Eds.), *The World of the Oxus Civilization*, Routledge, London, pp. 827-
12 861.

13 Pigott, V.C., 2011. Sources of Tin and the Tin Trade in Southwest Asia: Recent Research
14 and its Relevance to Current Understanding, in: Betancourt P.P., Ferrence S.C. (Eds.),
15 *Metallurgy: understanding how, learning why, studies in honor of James D. Muhly*,
16 *Prehistory Monograph* 29. INSTAP Academic Press, Philadelphia, pp. 273-291.

17 Pigott, V.C., 2004. On the importance of Iran in the Study of Prehistoric Copper-Base
18 Metallurgy, in: Stöllner, T., Slotta, R., Vatandoust, A., (Eds.), *Persia's ancient splendour*,
19 *mining, handicraft and archaeology*. Deutsches Bergbau-Museum, Bochum, pp. 28-43.

20 Pigott, V.C., Rogers, H.C., Nash, S.K., 2003. *Archaeometallurgical Investigations at Tal-e*
21 *Malyan: The Evidence for Tin-Bronze in the Kaftari Phase*, in: Miller, N.F., Abdi, K.
22 (Eds.), *Yeki Bud, Yeki Nabud: Essays on the archaeology of Iran in honor of William M.*
23 *Sumner*, University of Pennsylvania Museum of Archaeology and Anthropology,
24 Philadelphia, pp. 161-175.

25 Pigott, V.C., Howard, S.M., Epstein, S.M., 1982. Pyrotechnology and Culture Change at
26 Bronze Age Tepe Hissar (Iran), in: Wertime, Th.A., Wertime, S.F. (Eds.), *Early*
27 *Pyrotechnology: the evolution of the first fire-using industries*, Smithsonian Institution
28 Press, Washington D.C., pp. 215-236.

1 Porada, E., 1964. Nomads and Luristan Bronzes: Methods Proposed for a Classification of
2 the Bronzes, in: Mellink, M. J., (Ed.), Dark Ages and Nomads c. 1000 B.C., Istanbul, pp.
3 9-31.

4 Pollard, A.M., Bray, P., 2014. Chemical and Isotopic Studies of Ancient Metals, in:
5 Roberts B.W., Thornton, C.P. (Eds.), Archaeometallurgy in Global Perspective, Methods
6 and Syntheses. Springer, New York, pp. 217-238.

7 Potts, D.T., 1997. Mesopotamian civilization: the material foundations, Cornell University
8 Press, New York.

9 Rademakers, F.W., Farci, C. 2018. Reconstructing Bronze Production Technology from
10 Ancient Crucible Slag: Experimental Perspectives on Tin Oxide Identification. J. Archaeol.
11 Sci. Rep. 18, 343-355.

12 Rademakers, F.W., Rehren, Th., Pusch, E.B., 2018. Bronze Production in Pi-Ramesse:
13 Alloying Technology and Material Use, in: Ben-Yosef, E., (Ed.), Mining for Copper:
14 Essays in Memory of Professor Beno Rothenberg, Tel Aviv: University of Tel Aviv, pp.
15 503-525.

16 Rademakers, F.W., Verly, G., Somaglino, C., Degryse, P., 2020. Geochemical Changes
17 during Egyptian Copper Smelting? An Experimental Approach to the Ayn Soukhna Process
18 and Broader Implications for Archaeometallurgy. J. Archaeol. Sci. 122, 105223.

19 Radivojević, M., Pendić, J., Srejić, A., Korać, M., Davey, C., Benzonelli, A., Martínón-
20 Torres, M., Jovanović, N., Kamberović, Ž., 2018. Experimental Design of the Cu-As-Sn
21 Ternary Colour Diagram. J. Archaeol. Sci. 90, 106-119.

22 Rovira, S., Montero-Ruiz, I., Renzi, M., 2009. Experimental Co-Smelting to Copper-Tin
23 Alloys, in: Kienlin, T.L., Roberts, B., (Eds.), Metals and Societies Studies in Honour of
24 Barbara S. Ottaway, pp. 407-414.

25 Schmidt, E.F., Van Loon, M.N., Curvers, H.H., 1989. The Holmes expeditions to Luristan,
26 2 Vols., The Oriental Institute of The University of Chicago Publications 108, Chicago.

27 Scott, D.A., 2010. Ancient Metals: Microstructure and Metallurgy, Vol 1. Principles and
28 Practice, Conservation Science Press, Los Angeles.

- 1 Shafiei, B., 2010. Lead Isotope Signatures of the Igneous Rocks and Porphyry Copper
- 2 Deposits from the Kerman Cenozoic Magmatic Arc (SE Iran), and Their Magmatic-
- 3 Metallogenetic Implications. *Ore Geol. Rev.* 38, 27-36.
- 4 Thornton, C.P., 2009. The Chalcolithic and Early Bronze Age Metallurgy of Tepe Hissar,
- 5 Northeast Iran: A Challenge to the Levantine Paradigm. PhD dissertation, Department of
- 6 Anthropology, University of Pennsylvania.
- 7 Thornton, C.P., Lamberg-Karlovsky, C.C., Liezers, M., Young, S.M.M., 2002. On Pins and
- 8 Needles: Tracing the Evolution of Copper-Base Alloying at Tepe Yahya, Iran, via ICP-MS
- 9 Analysis of Common-Place Items. *J. Archaeol. Sci.* 29, 1451-1460.
- 10 Valério, P., Monge Soares, A.M., Silva, R.J.C., Araújo, M.F., Rebelo, P., Neto, N., Santos,
- 11 R., Fontes, T., 2013. Bronze Production in Southwestern Iberian Peninsula: the Late
- 12 Bronze Age Metallurgical Workshop from Entre Águas 5 (Portugal). *J. Archaeol. Sci.* 40,
- 13 439-451.
- 14 Vanden Berghe, L., 1987. Les Pratiques Funéraires à l'âge du Fer III au Pusht-i Kuh,
- 15 Luristan: les Nécropoles žgenre War Kabud. *Iran. Antiq.* 32, 201-66.
- 16 Vanden Berghe, L., 1981. Luristan: Vorgeschichtliche Bronzekunst aus Iran, Munich.
- 17 Vanden Berghe, L., 1971. Excavations in Pusht-i Kuh (Iran) Tombs Provide Evidence on
- 18 Dating "Typical Luristan Bronzes". *Archaeology* 24, 263-271.
- 19 Vatandoost-Haghighi, A., 1977. Aspects of Prehistoric Iranian Copper and Bronze
- 20 Technology, PhD Thesis. University of London, Institute of Archaeology.
- 21 Weeks, L., 1999. Lead Isotope Analyses from Tell Abraq, United Arab Emirates: New Data
- 22 Regarding the 'Tin Problem' in Western Asia. *Antiquity* 73, 49-64.
- 23 Weeks, L., 2004. Early Metallurgy of the Persian Gulf, Technology, Trade, and the Bronze
- 24 Age World, American School of Prehistoric Research Monograph Series, Brill Academic
- 25 Publishers Inc., Boston, Leiden.

Figure Captions

Figure 1- a) Map of Iran indicating the location of the Sangtarashan sanctuary in western Iran, as well as major archaeological sites and ore deposits mentioned in the paper, b) detailed map of Luristan and archaeological sites mentioned in the text.

Figure 2- a) Aerial view of the Sangtarashan region and location of the site at the north of the Sangtarashan village, b) Photo of the excavated area from the northern mountain, showing remains of the circular architecture of the Iron Age sanctuary, c) Architectural plan of Iron Age sanctuary discovered in six seasons of excavations at Sangtarashan.

Figure 3- a and b) Two examples of associated groups of bronze artefacts (caches) discovered during the first season of excavations at Sangtarashan, c) Drawing of some types of Sangtarashan bronze artefacts including vessels, axe-heads and sculptural artefacts.

Figure 4- Some metallic vessels and their selected samples analysed in this study.

Figure 5- Scatter plots of the concentrations of the main metallic elements in the composition of the Sangtarashan bronzes and copper alloys from other archaeological sites from Iron Age Iran, a and b) general and reduced range for Cu versus Sn, c and d) general and reduced range for Sn versus As, e and f) general and reduced range for Sn versus Pb.

Figure 6- Scatter plots of trace element concentrations in the composition of the Sangtarashan bronzes and other archaeological sites from the Iron Age of Iran, a) Ag versus Ni, b) As versus Sb. The reduced range scatter plots are provided to present potential correlations in details.

Figure 7- Three-isotope plot showing lead isotope ratios of the Sangtarashan samples. Three outlier samples are marked in the lead isotope graphs.

Figure 8- Three-isotope plots of lead isotope ratios for Sangtarashan and data available for archaeological sites (including copper alloys, slag, matte) and ore deposits from Iran, a and b) full isotope ratio range of all available data based on Table 5, c and d) reduced isotope ratio range of Sangtarashan artefacts and objects from other archaeological sites/collection, e and f) reduced isotope ratio range of Sangtarashan samples and ore deposits from the Iranian Plateau.