



Universiteit
Leiden
The Netherlands

Platinum surface instabilities and their impact in electrochemistry

Valls Mascaro, F.

Citation

Valls Mascaro, F. (2024, September 5). *Platinum surface instabilities and their impact in electrochemistry*. Retrieved from <https://hdl.handle.net/1887/4054933>

Version: Publisher's Version

License: [Licence agreement concerning inclusion of doctoral thesis in the Institutional Repository of the University of Leiden](#)

Downloaded from: <https://hdl.handle.net/1887/4054933>

Note: To cite this publication please use the final published version (if applicable).

2 Nucleation and Growth of Dendritic Islands during Platinum Oxidation-Reduction Cycling

Abstract

Platinum is the model catalyst in fuel cells because of its high activity towards oxygen reduction and hydrogen oxidation. However, its applicability is limited due to the degradation of the catalyst under operating conditions. This degradation process has been extensively studied by repeatedly oxidizing and reducing the electrode, which leads to the roughening of the surface due to the nucleation and growth of platinum nano-islands. Although the general picture of this surface roughening is well known, the atomic details concerning the nucleation and early growth of the islands are still under debate. In this work, we use Density Functional Theory (DFT) to calculate formation energies and diffusion barriers of an adatom, in both the unoxidized and the oxidized state, with the aim to provide further insight into the nucleation phenomena. Moreover, we analyze the shape of the nano-islands during the first stages of growth from images obtained experimentally with an Electrochemical Scanning Tunneling Microscope (EC-STM). Our results show not only that the islands form during the reduction of the surface, but also that they grow with a dendritic island shape, similarly to the platinum islands formed in vacuum by Molecular Beam Epitaxy (MBE).

2.1 Introduction

In heterogeneous catalysis, the surface structure of the catalyst plays a crucial role, as it determines not only the product selectivity and activity, but it also influences its stability [1–3]. This is especially the case for electrochemical reactions that are highly surface sensitive, such as the Oxygen Reduction Reaction (ORR) on platinum, which activity in acid is higher on stepped surfaces than on Pt(111) [4, 5].

Platinum is the model catalyst to be used not only in fuel cells, due to its high activity towards ORR and hydrogen oxidation [6–8], but also in electrolyzers to carry out the Hydrogen Evolution Reaction [9]. However, its economic feasibility is limited, as platinum is scarce, expensive and degrades upon fuel cell operation [10]. In order to obtain a better understanding of the reaction and the degradation mechanisms, it is crucial to observe the platinum surface structure under conditions as similar as possible to fuel cell operation. In the end, this would allow designing a better catalyst.

Cyclic oxidation-reduction of a platinum electrode is often used as a test for catalyst stability, as it simulates the switching *On* and *Off* of a fuel cell [11–13]. On Pt(111), this results in the formation of adatoms and vacancies, which leads to the nucleation and growth of platinum nano-islands (first only in 2D and later predominantly in height, thus 3D) [14–25]. The island growth involves the creation of step sites at the expense of terrace sites, which leads to a higher electrochemical signal for hydrogen adsorption/desorption [25, 26] and to a higher ORR activity, as specific sites near the step edges are more reactive towards the ORR [1]. The amount of step sites created depends not only on the number of islands present and their size, but also on their shape. The former two are correlated by the nucleation density: a larger number of nuclei requires the distribution of the adatoms among more islands that are, consequently, smaller. The nucleation density scales with F/M , where F is the flux of depositing atoms (i.e. in analogy to the deposition rate in Molecular Beam Epitaxy (MBE)) and M is the adatom mobility. During growth, the 2D island shape differs from the standard equilibrium Wulff-shape [27–29]: while in thermodynamic equilibrium the 2D island shape is defined by the minimum of the total step free energy [30], the (kinetic) growth Wulff-shape depends on the anisotropic step kinetics (i.e. different orientations along the island perimeter experience different growth speeds) [31, 32]. Therefore, the 2D growth shape significantly depends on the atom diffusion along the island perimeter, and thus the steps, as well as around the according kink and corner sites [33–35]. In addition, it also depends on the rate, with which the adatoms reach the island edge [36, 37]. Enhancing the atom diffusion along the island perimeter, e.g. by raising the temperature, leads to more compact islands, while increasing the flux leads to islands with a larger number of branches, often called dendrites [30, 38, 39].

Previously, it was reported that the islands formed upon oxidation-reduction cycling of a Pt(111) electrode are hexagonal, and their steps and facets were identified and correlated with the different peaks in the hydrogen adsorption/desorption fingerprint (i.e. below 0.4 V in the Cyclic Voltammogram, see Fig. 2.1) [26]. However, it is known that Pt islands formed by MBE at low temperatures (≤ 300 K) [30, 37–39] grow dendritically. This dissimilarity is relevant, as the island shape effects the electrochemical activity: if the islands formed upon

oxidation-reduction would also grow dendritically, the earlier assignation of the peaks in the hydrogen adsorption/desorption region to the different steps and facets surely would need to be reconsidered. Moreover, it is still a puzzle when these islands exactly nucleate, as they could, until now, only be observed with a Scanning Tunneling Microscope (STM) when the surface was reduced, but not during the oxidation [24, 40], in which additional atoms are pushed out onto the surface [17, 41].

To address these issues, here we study the thermodynamics and kinetics of island nucleation by using formation and diffusion barriers calculated with Density Functional Theory (DFT). Our results show that nucleation takes place during the cathodic sweep, rather than during oxidation. Moreover, we analyze the island shape during early growth by measuring their perimeter and area, from which we finally determine the island compactness and a factor describing the additional step lengths. Contrary to what was suggested in [26], our observations provide evidence that the growth of the islands results in dendritic island shapes.

2.2 Experimental

Electrochemistry. The cyclic voltammograms were recorded in a three-electrode glass cell using a reversible hydrogen electrode (RHE) as the reference, a Pt wire (MaTeck, Germany) as a counter, and a Pt(111) crystal (with a purity of 99.999 % and polished $< 0.1^\circ$, Surface Preparation Laboratory, The Netherlands) as the working electrode. Prior to the experiments, we left the glassware overnight in an acidified potassium permanganate solution and cleaned it afterwards with diluted piranha, before finally boiling it five times in ultrapure water ($> 18.2 \text{ M}\Omega \text{ cm}$, Millipore Milli-Q). Similarly to sputtering and annealing in vacuum, we first etched the Pt(111) sample electrochemically (125 cycles at 50 Hz, $\pm 2 \text{ V}$ versus Pt) in an acidified 2.5 M CaCl_2 solution, before flame annealing (3 min at around 1250 K) and cooling down in a 1:4 H_2/Ar mixture. We repeated this procedure three times before each experiment. To develop a denuded, (bulk) contamination free interface zone, we performed the last annealing step at slightly lower temperature (approximately 50 K less). The measurements were performed in an Ar-purged 0.1 M HClO_4 solution (Merck Suprapur) using a potentiostat from Bio-Logic (VSP-300).

Electrochemical Scanning Tunneling Microscopy. We recorded the STM images with a home-built Electrochemical Scanning Tunneling Microscope (EC-STM) described previously [42–45]. The reference electrode used was a RHE, the counter was a Pt coil, and the working electrode was the same Pt(111) crystal described above. The STM tips were electrochemically etched from a $\text{Pt}_{90}\text{Ir}_{10}$ wire and coated with electrophoretic paint (Clearclad HSR) as well as polyethylene to minimize the faradaic contributions in the tunneling current. The cleaning procedure of the glassware is described in Ref. [25]. To reduce the oxygen concentration in the electrolyte, we de-aerated it with N_2 before measuring for at least 3 hours. At the beginning of each experiment, we checked the surface quality and cleanliness first by cyclic voltammetry and then by scanning large surface areas with the STM.

DFT calculations. Using Density Functional Theory (DFT), we calculated the Gibbs free formation energy of a Pt-adatom and PtO_2 -adatom (i.e. strictly speaking, a PtO_2 -

admolecule) on Pt(111) as well as the Gibbs free adsorption energy of oxygen onto Pt step and kink sites. The DFT simulations were performed using the Vienna Ab-Initio Simulations Package [46–48]. A plane wave basis set was used with an energy cutoff of 450 eV and the ion core potentials were modelled using the projector augmented wave (PAW) approach. The PW91 exchange-correlation functional was used [49]. We modeled the surface as a four-layer slab, with the bottom two layers frozen at the experimentally measured lattice constant of Pt (3.92 Å [50]). The Pt(111) surface was modeled with 5x5 and 7x7 unit cells. We used the energy of an additional Pt atom attached directly to a kink site on Pt(632) as a reference for the formation energy determination of a PtO₂-adatom. The Pt(632) surface was modeled in a 1x1 unit cell. Monkhorst-Pack mesh k-space sampling grids were used [51]. A 3x3x1 mesh grid was used for both the 5x5 and 7x7 Pt(111) unit cells, and a 7x7x1 grid was used for the 1x1 Pt(632) surface. We optimized the geometry until the forces on each atom were less than 0.02 eV Å⁻¹, and included dipole correction in the surface normal direction [52].

To calculate the potential-dependent Gibbs free formation energy of a PtO₂-adatom on Pt(111), we modeled the reaction equations 2.3-2.5 in the Results section. We calculated the Gibbs free energy change for each reaction from $\Delta G = \sum G_{products} - \sum G_{reactants}$, where G stands for the Gibbs free energy of each species calculated at 300 K and 1 bar. For the adsorbed species we accounted only for vibrational energy and entropy terms, whereas for the gas phase species (hydrogen and water) we included all contributions to the free energy consisting of vibrational, rotational, and translational energy. The Gibbs free energies of adsorption and formation were calculated relative to aqueous water and protons using the computational hydrogen electrode method [7] and procedures described previously [53]. The Gibbs free energy of the gas phase water was evaluated at its experimentally measured vapor pressure at 300 K; under conditions where it is in equilibrium with liquid (aqueous) water.

We calculated the oxygen adsorption at step as well as kink sites on Pt(632) as a function of oxygen coverage: the structures evaluated were based on those found to be most stable by Fantauzzi et al [54].

We calculated the diffusion barrier for a Pt-adatom on Pt(111) using the climbing-image nudged elastic band method [55]. The transition state was identified when, for the highest energy image, the forces on each of the atoms and the tangent force were below 0.02 eV Å⁻¹ and the tangent forces on the preceding images were opposite in sign to the those on the images following the transition state image. The transition state vibrational modes were also examined, and showed one imaginary frequency along the reaction path. Diffusion was examined from the most stable, fcc, adsorption site to the second most stable, hcp, site.

2.3 Electrochemical Measurements

Figure 2.1 shows in red the Cyclic Voltammogram (CV) of the pristine Pt(111) surface in a 0.1 M HClO₄ solution measured between 0.06 and 0.85 V, and in orange the first Oxidation-Reduction Cycle (ORC) measured up to 1.35 V. The region below 0.4 V, attributed to hy-

drogen adsorption/desorption, changes during the next 200 ORCs due to the creation of (111) and (100) steps (which more precisely should be formulated as $\langle 110 \rangle / \{111\}$ and $\langle 110 \rangle / \{100\}$, that is, steps along a direction equivalent to [110], with either {111} or {100} microfacets) [26, 56–60]. The increase in the number of step sites with increasing cycle number also becomes evident from the potential window between 0.8 and 1.0 V, where step oxidation takes place, leading also there to an increase of the electrochemical current [61, 62].




Figure 2.1: Oxidation-Reduction Cycles on Pt(111). The CV to only 0.85 V and the first ORC are shown in red and in orange, respectively, while the remaining ORCs are indicated according to the color scale. The OH adsorption, step oxidation, PE_{rev}, and PE_{irr} regions are indicated, as well as the voltage at the critical coverage. The scan rate is 50 mV s⁻¹.

Focusing now on the terraces, the first step towards (but still prior to) terrace oxidation is the adsorption of OH that takes place between 0.5 and 0.8 V [63, 64]. At higher potentials, the OH_{ad} is converted into O_{ad}, which subsequently interchanges position with the platinum surface atoms in the so-called reversible Place Exchange (PE_{rev}) [65]: concretely, at least 1, but most likely 2 oxygen atoms go subsurface underneath a Pt atom, which they lift vertically up to nearly one atomic distance in height [41, 66–72]. This process results in the pronounced peak at around 1.06 V [73, 74]. Its position shifts to higher potentials with faster scan rates, indicating that either the conversion of OH_{ad} to O_{ad}, or the place-exchange, or both are kinetically limited [41, 75–77].

The coverage of lifted PE_{rev} atoms rises with increasing electrode potential, leading to an increase of the surface stress [65]. If the upper (vertex) potential during the ORCs is held below 1.17 V [41] (or below 1.25 V, according to You et al. [78]), no structural changes take place upon reduction: all hovering PE_{rev} atoms fall back into their vacancies, and the original, flat Pt(111) surface is fully restored [41, 72, 77–79]. This changes completely if the

Chapter 2. Nucleation and Growth of Dendritic Islands during Platinum Oxidation-Reduction Cycling

upper potential is increased beyond the critical value, which implies also that a critical coverage of PE_{rev} atoms is surpassed [65]. At this moment the surface stress becomes so large that, instead of creating new PE_{rev} atoms, the next atoms created by the PE mechanism are no longer hovering above their vacancies; instead they are displaced on top of the terrace, thus becoming real adatoms, which we call PE_{irr} atoms or PtO_2 -adatoms as they do get oxidized [17, 41, 65]. Upon reduction, the surface is no longer restored during the cathodic sweep, as the adatoms formed during the PE_{irr} nucleate into islands before finding their way back to their original sites, i.e. before annihilating with their vacancies [80]. This is also favored by the Ehrlich-Schwoebel barrier [81, 82], which makes it more difficult for the adatoms to hop-down the descending step and fall into the vacancy, although it is known that the Ehrlich-Schwoebel barrier breaks down for small terraces [83] and for downhill transport mediated by kinks [84, 85]. This irreversible regime is responsible for the roughening, the island formation, and thus the changes in the CV during the ORCs.

It was concluded that the PE_{rev} takes place randomly similar to a 2D adatom gas. However, the formation of a semi-ordered oxide structure, like local 1D chains, can not be fully excluded [41, 71]. The latter would match with the fact that rows of PtO_2 units have been observed on Pt(111) with STM in "vacuum" under 1 bar of oxygen pressure and at 529 K [86]. In addition, the stability of rows at electrochemical potentials, similar to the ones for oxygen adsorption, was supported by DFT [87]. The formation of the rows during the PE_{rev} would also explain the existence of a critical coverage and potential, see above. It would result in an increase of the surface stress (i.e. as a consequence of the lattice mismatch between Pt(111) and PtO_2), which becomes larger as the rows grow in length. Once the critical stress is surpassed, the PE_{irr} starts, and one PE_{irr} atom per row is pushed out onto the terrace, thereby decreasing the local surface stress [65].

Van Spronsen et al. [86] observed that these oxide rows, or "spokes", arrange in "spoke-wheel" structures with hexagonal symmetry: triangles of spokes delimiting triangular terraces. Figure 2.2a shows an ideal, fully ordered spoke-wheel structure, in which each of the spokes consists of 8 elevated PtO_2 units (PE_{rev} atoms), at the expense of 9 Pt surface atoms. The length of a row consisting of 8 PtO_2 coincides almost exactly with the length of a row of 9 Pt surface atoms, and thus the surface stress is minimum in this configuration. The "missing" Pt atom per spoke is pushed out onto the triangular terraces during the PE_{irr} , creating a PtO_2 -adatom. On average, this results in 1.5 PtO_2 -adatoms formed in each triangle (i.e. two PtO_2 -adatoms in every second triangle, while only one adatom in the other triangles) and hence a total of 9 adatoms formed per spoke-wheel. However, in reality, the spokes might not arrange into perfect spoke-wheels: some degree of disorder is present that is either caused by entropy or by a kinetic limitation during their formation (see Fig. 2.2b) [86].




Figure 2.2: The Irreversible Place-Exchange Regime. The Pt atoms of the original, flat terrace are colored in dark blue, the lifted Pt_{rev} atoms in light blue, forming spokes or rows, the oxygen atoms in orange, and the Pt_{irr} atoms that are pushed onto the terrace, thus becoming PtO_2 -adatoms, in dark red. The PtO_2 -adatoms lead eventually to the growth of the nano-islands. (a) shows one fully ordered spoke-wheel structure without any disorder present. However, from [41, 71, 86] we know that, probably due to entropy, a certain degree of disorder is present. Therefore, (b) shows an impression of a disordered spoke-wheel phase: elements of the original triangles are still visible, in which the PtO_2 -adatoms, the Pt_{irr} atoms, are *trapped*.

2.4 Formation of Adatoms and Adatom Islands

As the PtO_2 -adatoms are formed during the PE_{irr} , one naturally would assume that the formation of the adatom islands takes place also during this regime. However, two independent STM studies stated that the islands can not be observed during the oxidation up to 1.3 V, but become visible only when the surface is subsequently reduced [24, 40]. There are two possible explanations for this. The first one is that the PtO_2 islands are actually present already at 1.3 V, but can not be easily identified with an STM. This is because the Local Density of States (LDOS) of PtO_2 is significantly lower than the LDOS of bare platinum, leading to a major decrease in the tunneling current, and hence a lower apparent height than the 1 ML height expected (if tunneling *filled states*). Moreover, it might be almost impossible to distinguish between PtO_2 -adatom islands and the PE_{rev} atoms, as the latter are also lifted nearly 1 ML from the surface, and also do have a different LDOS than the bare platinum. Wakisaka et al. reported that the Pt(111) surface becomes bumpy during the anodic sweep where tiny dots appear that are lifted around half a monolayer in height. It could be that these dots are the PE_{rev} atoms, but it might also very well be that they are irreversible, pushed out PtO_2 -adatoms, or even small PtO_2 -adatom islands that will become larger upon further growth. The second possible explanation, to why the islands could not be observed with an STM during the oxidation, is that indeed the islands are not formed until the surface is reduced. Even if the PtO_2 -adatoms are formed during the PE_{irr} regime, whether these PtO_2 -adatoms nucleate into islands depends both on their concentration and their mobility, such that thermodynamic as well as kinetic considerations have to be taken into account.

In order to provide further insight into the precise formation of the islands, we applied DFT to extract thermodynamic formation energies and kinetic diffusion barriers, all of which are important in the nucleation of Pt- as well as PtO_2 -adatoms into islands, on both an oxidized as well as reduced Pt(111) surface.

2.4.1 Thermodynamic Requirements for Nucleation

In order to study the nucleation of adatom islands, we need first to introduce the chemical potential of adatoms, which is described as follows [88]:

$$\mu_{ad} = \mu_0 + k_B T \ln\left(\frac{\theta_{ad}}{1-\theta_{ad}}\right) + W(\theta_{ad}) \approx \mu_0 + k_B T \ln(\theta_{ad}) \quad (2.1)$$

where μ_0 is the ground state energy of an adatom (and thus the adatom formation energy), k_B is the Boltzmann constant, T is the temperature, θ_{ad} is the adatom concentration on the surface, and $W(\theta_{ad})$ describes the interaction energy between adatoms. The entropy term $k_B \ln\left(\frac{\theta_{ad}}{1-\theta_{ad}}\right)$ accounts for the number of free sites where an adatom can be placed (i.e. similarly to the entropy term in a Langmuir isotherm) and can usually be approximated to $k_B \ln(\theta_{ad})$, as in most cases the adatom concentration is very low. Moreover, the adatom interaction term $W(\theta_{ad})$ is small in comparison to the other terms such that it can typically be neglected, especially for low coverages.

Thermodynamic equilibrium requires the equilibration of all chemical potentials such

that the surface will maintain the equilibrium adatom concentration ($\theta_{eq,ad}$) by a balanced mass transport of adatoms from step- and, in particular, kink-sites to the terraces and back.

At constant temperature, changes in the actual adatom concentration (θ_{ad}) are only possible during surface growth (or etching), which originates from the increased (decreased) chemical potential created by the additional flux of adatoms (or vacancies) during, e.g. an MBE (or sputtering) experiment.

When surface growth (or etching) stops, the surface will pursue to reestablish the thermodynamic equilibrium. If θ_{ad} is lower than $\theta_{eq,ad}$, the equilibrium is restored by the formation of additional adatoms that detach from kinks and diffuse onto the terrace. If on the other hand, θ_{ad} is higher than $\theta_{eq,ad}$, adatoms on the terrace quickly diffuse towards the steps, where they finally get incorporated at kinks. At too high deposition flux, where the surface no longer will revert back to its lowest free energy configuration, adatoms find each other before encountering the steps during their random walk (which depends on the flux, the mobility, and their distance to the step), and nucleate into adatom islands to locally lower the enhanced chemical potential. Neglecting for the moment any kinetic arguments we can therefore conclude that nucleation is only possible if $\theta_{ad} \gg \theta_{eq,ad}$.

Realizing the importance of the equilibrium Pt-adatom background pressure, $\theta_{eq,Pt,ad}$, on the thermodynamics of nucleation, one can calculate $\theta_{eq,Pt,ad}$ by using the Boltzmann equation:

$$\theta_{eq,Pt,ad} = \exp\left(-\frac{E_{Pt,ad}}{k_B T}\right) \quad (2.2)$$

in which $E_{Pt,ad}$ is the formation energy of a Pt-adatom, defined as the energy required to take an atom from a kink site and place it onto the terrace, and T is room temperature, $T = 298$ K.

As estimated from our DFT calculations, $E_{Pt,ad}$ is 1.2 eV independently of the electrode potential (see the orange line in Fig. 2.3a). This gives rise to a potential-independent equilibrium adatom density of only $\theta_{eq,Pt,ad} = 5 \cdot 10^{-21}$, shown with the orange line in Fig. 2.3b. Therefore, the use of the Boltzmann equation, which includes the approximation in the entropy term explained before and neglects the adatom-adatom interaction, is well justified (see Appendix A for further details). As usual, the numbers obtained from DFT should be taken with some care, due to the inherent error margin of this methodology. However, the order of magnitude is typically captured correctly. In this work, the effect of near-surface solvation on the formation of a Pt- or PtO₂-adatom has not been considered, and while we expect it to have small influence on the energy difference between a Pt- and a PtO₂-adatom on Pt(111) (as the magnitude of the surface-normal dipole moments are small), this should be evaluated in future work. In our case, however, the error associated does not change significantly the atomic picture, and hence the message is still the same. With a typical error of 0.2 eV, $E_{Pt,ad}$ would be 1.0 eV instead of 1.2 eV, resulting in $\theta_{eq,Pt,ad} = 10^{-17}$, which is still very low.

From Fig. 2.1 we know that first the steps, and then the terraces oxidize. This is expected, as lower coordinated sites (i.e. the steps) bind an oxygen atom more strongly [1]. Similarly, considering the oxidation of Pt-adatoms, which to our knowledge has not been

Chapter 2. Nucleation and Growth of Dendritic Islands during Platinum Oxidation-Reduction Cycling







Figure 2.3: Formation Energies and Concentrations of Adatoms. (a) The formation energies of a Pt-adatom and a PtO₂-adatom on Pt(111), and a PtO₂-adatom on a Pt(111) with 4/25 ML O_{ads}, are shown in orange, red, and blue, respectively. They are referenced with respect to the binding energy of an additional Pt atom attached to a kink site on Pt(632), which can be unoxidized (green dashed line) or oxidized (pink dashed line). The numbers in brackets indicate the reactions considered, as explained in the main text. The vertical dotted red and purple lines indicate the Pt-adatom oxidation potential and the potential at which $E_{PtO_2,ad}$ (1&2) becomes zero, respectively. The first ORC is shown in dotted light blue and the different regions are indicated. (b) Equilibrium Pt- and PtO₂-adatom concentrations calculated from (a). The dotted red and blue lines result from the Boltzmann equation which match, respectively, the solid red and blue lines (considering the entropy term without approximation) at potentials < 0.85 V. The dashed black line and the arrows indicate the path followed upon one ORC, while the vertical lines indicate the potentials used in Table 2.1. (c) Zoomed-in graph of the region between 0.85 V and 1.00 V in (b). (d) Concentration ratios between PtO₂- and Pt-adatoms.

studied before, one would expect them to oxidize before 0.8 V, during the anodic sweep. Consequently we have calculated, using DFT, the energy required to form a PtO₂-adatom

from a kink site. In general, we have to distinguish three different reaction pathways. In the first one (see eq. 2.3 below), a pure Pt adatom (see Fig. 2.4b) is created from a kink-atom at an unoxidized step ($Pt_{ad}/kink/Pt(632)$ in Fig. 2.4a), and oxidizes immediately when diffusing onto the terrace, leading to a PtO_2 -adatom (Fig. 2.4c). In the second one (eq. 2.4), a PtO_2 -adatom is created from a Pt atom at a kink on an oxidized step ($Pt_{ad}/kink/Pt(632)_{ox-steps}$ in Fig. 2.4d), while taking with it two oxygen atoms such that the remaining "empty" kink site has to be reoxidized. Finally, in the third reaction pathway (eq. 2.5) both the steps and the terraces are oxidized, and the PtO_2 -adatom is created from a kink ($Pt_{ad}/kink/Pt(632)_{ox-steps}$) by placing such a unit onto the terrace (see Fig. 2.4e).



where the slash stands for "at", e.g. $Pt_{ad}/kink/Pt(632)$ stands for a Pt-adatom at a kink site at a Pt(632) surface, and "ox" stands for "oxidized".




Figure 2.4: Ball Models of Step and Adatom Configurations. (a) Bare platinum step on a Pt(632) surface, which was used to calibrate the total energy scale via the Pt-adatom at the kink site. (b) Pt-adatom on an fcc site on a Pt(111) terrace. (c) PtO_2 -adatom on a bridge site on a Pt(111) terrace. (d) A fully oxidized step forming PtO_2 oxide chains similar to the spokes on the terraces [89,90]. (e) PtO_2 -adatom on a bridge site on a Pt(111) terrace that is covered with a perfectly ordered 4/25 ML O_{ads} superstructure.

Figure 2.3a shows in red the potential-dependent formation energy of a PtO_2 -adatom on Pt(111). As this energy is the same for both reaction pathways, creation from an unoxidized step (eq. 2.3) and from a fully oxidized step (eq. 2.4), we consider both cases together and name the corresponding formation energy $E_{PtO_2,ad}$ (1&2). We used the energy of an additional Pt atom attached directly to a kink site on Pt(632) as a reference for the formation energy of a PtO_2 -adatom. As we find that the formation energy of an adatom is nearly the same whether we reference an oxidized or a non-oxidized kink site on Pt(632), we have de-

Chapter 2. Nucleation and Growth of Dendritic Islands during Platinum Oxidation-Reduction Cycling

cided to independently consider adatom formation and Pt(632) step/kink oxidation. Moreover, as we calculate the adatom formation energy with a constant oxygen coverage in our reference state, both oxidized and non-oxidized kink reference states have the same energy, see Fig. 2.3a. We have separately plotted the thermodynamics of the oxidation of step/kink sites on Pt(632) as a function of oxygen coverage along the step in Fig. A.2, in Appendix A. A 3-dimensional plot would be required to simultaneously consider varying the adatom coverage and the oxygen coverage. We leave this for future work, but do not expect it to affect our conclusions, again given that the adatom formation energy from an oxidized kink at constant oxygen coverage is not significantly different to that from a bare kink.

As the formation energies $E_{PtO_2,ad}$ (1&2) cross $E_{Pt,ad}$ at 0.59 V, this defines the equilibrium potential at which the Pt-adatoms oxidize to PtO_2 -adatoms, according to:



Equipped with the potential dependent formation energy, $E_{PtO_2,ad}$ (1&2), we calculate the equilibrium concentration of PtO_2 -adatoms, $\theta_{eq,PtO_2,ad}$ (1&2), again by using the Boltzmann equation. As $E_{PtO_2,ad}$ (1&2) decreases with potential, $\theta_{eq,PtO_2,ad}$ (1&2) increases, see the red line in Fig. 2.3b. Consequently, above 0.59 V the ratio $\frac{\theta_{eq,PtO_2,ad}(1\&2)}{\theta_{eq,Pt,ad}}$, which gives an indication for the driving force to oxidize a Pt-adatom, becomes larger the higher the potential is: while at 0.59 V it is equal to 1 (equal concentration of Pt-adatoms and PtO_2 -adatoms), it is already a factor 8000 higher at 0.65 V, see the red line in Fig. 2.3d. As the potential increases further, $E_{PtO_2,ad}$ (1&2) becomes larger, up to the point that the Boltzmann equation results in $\theta_{eq,PtO_2,ad}$ (1&2) = 1 at 0.90 V, and even adatom concentrations larger than 1 ML at potentials above (see the dotted red line in Fig. 2.3b). The Boltzmann equation does not hold at these high adatom coverages. However, in first instance this can be solved by using the full entropy term in the adatom chemical potential equation, $k_B \ln(\frac{\theta_{eq,ad}}{1-\theta_{eq,ad}})$, instead of the approximation to $k_B \ln(\theta_{eq,ad})$ (see Appendix A). The equilibrium adatom concentration is then given by:

$$\theta_{eq,Pt,ad} = \frac{\exp(\frac{-E_{ad}}{k_B T})}{1 + \exp(\frac{-E_{ad}}{k_B T})} \quad (2.7)$$

In Appendix A, we evaluate the error one makes when using the Boltzmann approximation and show that it is as low as $6 \cdot 10^{-4}$ for $\theta_{eq,PtO_2,ad}$ (1&2) up to 0.85 V.

By using the equation with the full entropy term, we now see in Fig. 2.3b that the equilibrium adatom concentration asymptotically approaches 1 ML with increasing potential. However, one has to realize that at these high coverages the definition of the adatom gas is no longer valid. Single, individual adatoms do only exist up to a coverage of 0.25 ML, as at higher coverages one connects at least 3 into a cluster. As the relative error between the Boltzmann approximation and the full solution is only 25 % at 0.25 ML, which is 0.25 ± 0.06 ML, the equilibrium adatom density is (for most applications) sufficiently well described already by the Boltzmann approximation.

Nevertheless, it is conceptually still interesting to consider the meaning of reaching a coverage of 1 ML. This situation is probably most comparable to the roughness transition

on surfaces, where at high enough temperatures the step free energy crosses zero and the surface can create as many steps as desired [91–95]. Derived from the chemical potential with a kink site as reference, 1 ML of coverage at 0.94 V implies the formation of a complete oxide layer. It is striking that the PE_{rev} starts around this potential, which describes the first part of the terrace oxidation [78].

We know from Fig. 2.1 and Refs. [61, 62] that the steps begin to oxidize at 0.8 V, and that full oxidation happens as late as 1.05 V, probably leading to oxide chains as observed in vacuum [89, 90]. Therefore, we also consider the situation in which a PtO_2 -adatom is formed from a fully oxidized step (kink). As the formation energy, as explained before, is the same independently of whether the step is unoxidized or fully oxidized, it is still described by the red line in Fig. 2.3a. However, even if the thermodynamics of PtO_2 -adatom formation do not change, the kinetics surely do. As a fully oxidized step forms a 1D- PtO_2 row, we expect that detaching a PtO_2 -kink atom from such a step involves overcoming a significant barrier, and is thus kinetically limited (i.e. the PtO_2 -kink atom has to “diffuse” out of the step). Consequently, $\theta_{eq, PtO_2, ad}$ (1&2) will not be reached (although, strictly speaking, it always would when given enough time) and, as then $\theta_{PtO_2, ad}$ (1&2) < $\theta_{eq, PtO_2, ad}$ (1&2), nucleation will not occur. Furthermore, even if this kinetic barrier is small, to reach 1 ML PtO_2 -adatoms the steps would need to retract with the same width. This would involve a large mass transport and thus require a very long time, i.e. $1.5 \cdot 10^5$ PtO_2 -kink atoms need to be detached from the step to create 1 ML PtO_2 -adatoms on a $100 \times 100 \text{ nm}^2$ terrace.

At 1.17 V the PE_{irr} starts, leading to the formation of PE_{irr} atoms. As the terrace is then oxidized, we calculated also the formation energy of a PtO_2 -adatom on a terrace covered with $4/25$ ML O_{ads} , which we named $E_{PtO_2, ad}$ (3), see eq. 2.5 and the blue line in Fig. 2.3a. By comparing $E_{PtO_2, ad}$ (3) with $E_{PtO_2, ad}$ (1&2), it is evident that, once the terraces oxidize, it becomes energetically more expensive to form PtO_2 -adatoms. Consequently, the equilibrium PtO_2 -adatom concentration $\theta_{eq, PtO_2, ad}$ (3) is lower than $E_{PtO_2, ad}$ (1&2) at every given potential. Based on this result, we expect that the potential dependent formation energy of the PtO_2 -adatoms shifts to even higher potentials the more the terrace is oxidized.

As there is a large driving force towards adatom oxidation, with $\frac{\theta_{eq, PtO_2, ad} (3)}{\theta_{eq, Pt, ad}} = 2 \cdot 10^{20}$ at 1.17 V), the PE_{irr} atoms are surely oxidized, thus PtO_2 -adatoms. Mechanistically, there are two possible pathways for the formation of PtO_2 -adatoms from the PE_{irr} : either the newly lifted PE_{rev} atoms are pushed out directly onto the terrace, where they immediately oxidize, or the PE_{rev} atom first tries extending an oxide row but then it is pushed onto the surface together with 2 oxygen atoms, due to the too high stress in the row. At 1.17 V, as well as at 1.35 V (the upper vertex potential during our ORCs) $\theta_{eq, PtO_2, ad}$ (3) is practically 1 ML. However, the actual concentration of PtO_2 -adatoms formed during the PE_{irr} is only 0.0245 ML, obtained from a fit of the roughening evolution during 170 ORCs up to 1.35 V [80]. As 0.0245 ML is much lower than the 1 ML of critical coverage, even at 1.35 V the PtO_2 -adatoms created will not nucleate into islands.

The situation changes completely during the backward (cathodic) sweep. Following the dashed black line in Fig. 2.3b from right to left, $\theta_{eq, PtO_2, ad}$ (3) decreases with decreasing potential. At 0.94 V, $\theta_{eq, PtO_2, ad}$ (3) becomes equal to $\theta_{PtO_2, ad}$, thus 0.0245 ML. Therefore,

Chapter 2. Nucleation and Growth of Dendritic Islands during Platinum Oxidation-Reduction Cycling

upon decreasing the potential further, $\theta_{PtO_2, ad}$ needs to diminish in order to adapt to the decreasing equilibrium concentration $\theta_{eq, PtO_2, ad}$ (3), and hence the nucleation of PtO_2 -adatoms into PtO_2 -islands is now thermodynamically favorable. However, this still does not ensure that nucleation takes place, as one should also consider the kinetics, thus the mobility, of the PtO_2 -adatoms. If the PtO_2 -adatom diffusion is very slow, it will take a significant amount of time for the nucleation to occur. As the potential decreases even further, the equilibrium PtO_2 -adatom concentration ($\theta_{eq, PtO_2, ad}$ (3), or $\theta_{eq, PtO_2, ad}$ (1&2) once the terraces are reduced) drops lower, thus rising the driving force for nucleation. This situation holds until 0.59 V, when the PtO_2 -adatoms reduce back to Pt-adatoms and the equilibrium adatom concentration becomes constant. Anyhow, although $\theta_{eq, Pt, ad}$ is much lower ($= 5 \cdot 10^{-21}$) than the coverage of PtO_2 -adatom created during the PE_{irr} ($= 0.0245$ ML), the nucleation will still depend on kinetics, now on the mobility of the Pt-adatoms. Therefore, in order to solve the complete riddle, we also need to study the diffusion rates of both Pt- and PtO_2 -adatom species. We discuss this in more depth in the next section.

	0.36 V (E_{pzc})	0.59 V	0.90 V	1.17 V	1.35 V
$\theta_{eq, Pt, ad}$	$5 \cdot 10^{-21}$	$5 \cdot 10^{-21}$	—	—	—
$\theta_{eq, PtO_2, ad}$ (1&2)	$4 \cdot 10^{-36}$	$5 \cdot 10^{-21}$	0.5	—	—
$\frac{\theta_{eq, PtO_2, ad} (1\&2)}{\theta_{eq, Pt, ad}}$	$9 \cdot 10^{-17}$	1	$1 \cdot 10^{20}$	—	—
$\theta_{eq, PtO_2, ad}$ (3)	—	—	—	1	1
$\frac{\theta_{eq, PtO_2, ad} (3)}{\theta_{eq, Pt, ad}}$	—	—	—	$2 \cdot 10^{20}$	$2 \cdot 10^{20}$

Table 2.1: Pt- and PtO_2 -adatom Equilibrium Concentrations and their Ratios. We only provide relevant values at each of the potentials: if the terraces are not oxidized, we consider $\theta_{eq, PtO_2, ad}$ (1&2), while we consider $\theta_{eq, PtO_2, ad}$ (3) if the terraces are oxidized. E_{pzc} stands for potential of zero charge of Pt(111) [96,97].

2.4.2 Kinetic Requirements for Nucleation

As the probability for nucleation does not only depend on the supersaturation (i.e. how much the adatom concentration exceeds the equilibrium adatom concentration), we will in the following consider also the effects of (limited) adatom mobility. For nucleation to occur during the oxidation sweep, the PtO_2 -adatoms must diffuse over the terrace, find each other, and overcome the critical nucleus size, as only clusters larger than the critical nucleus size do not decay [37]. If the diffusion of the PtO_2 -adatoms is slow, then it will take longer times for the adatoms to find each other and therefore the nucleation will be delayed. In the extreme limit when diffusion is completely kinetically hindered, nucleation does never take place.

Using DFT, we calculated the diffusion barrier of a Pt-adatom on Pt(111), $E_{Pt,ad,Diff}$, to be 0.28 eV. This value is close to the 0.26 eV obtained in two different studies, one which combines STM with MC simulations [98] and the other one based on Field Ion Microscopy measurements [99], and not significantly far from the 0.16 eV calculated by an early Effective Medium Theory study [100]. Using this value, we can calculate an approximation of the Pt-adatom jump rate by using an Arrhenius-type equation:

$$\nu_{ad} = \nu_0 \exp \left(-\frac{E_{Pt,ad,Diff}}{k_B T} \right) \quad (2.8)$$

in which ν_{ad} is the jump rate and ν_0 is the attempt frequency, given by the vibrational frequency (10^{13} Hz) for single metal atoms. As a result, we obtain a Pt-adatom jump rate of 10^8 jumps/s.

We have also calculated the relative energy of a PtO_2 -adatom on a Pt(111) surface at different adsorption sites: bridge1, bridge2, atop, fcc and hcp (see Fig. 2.5). The most stable configuration is bridge1, which was used as reference to compare with the energetics of the others. Within the configurations calculated, a PtO_2 -adatom in bridge1 has an energy that is at least 0.78 eV lower than all other configuration considered. While these are just thermodynamic arguments, and further DFT calculations on the kinetics of PtO_2 -adatom diffusion would be beneficial (but are left for future work), the change in energy when moving from one site to another gives an estimate on the diffusion barrier, within the error margins that are characteristic from DFT. We expect the diffusion barrier of a PtO_2 -adatom to be at least as high as 0.78 eV, and obtain a PtO_2 -adatom jump rate of only 0.28 jumps/s, which is approximately 10^9 times less than the jump rate of a Pt-adatom. To demonstrate how slow this PtO_2 -adatom diffusion is, we estimate how many jumps one PtO_2 -adatom can perform during the cathodic sweep. Decreasing the potential from 1.35 V to 0.59 V (where PtO_2 -adatoms reduce to Pt-adatoms) with 50 mV/s leads to a reduction time of 15.2 s. In this time, a PtO_2 -adatom can only do 4 jumps. This is not enough to encounter other PtO_2 -adatoms, and therefore nucleation will not occur.




Figure 2.5: Potential Energy Landscape of a PtO_2 -adatom (PE_{irr} -adatom) on Pt(111): (a) bridge1, (b) atop, (c) fcc, (d) hcp, (e) bridge2. The lowest energy state, the energy of a PtO_2 -adatom at bridge1, is used as reference. The diffusion barrier of a PtO_2 -adatom must be at least 0.78 eV.

In addition to this extremely low jump rate, as the PE_{rev} involves the formation of spoke-wheels, the PtO_2 -adatoms formed during the PE_{irr} will be “trapped” within the triangular areas. The reason for this is that the spokes delimiting the triangles are lifted nearly one monolayer high above the terrace, preventing the PtO_2 -adatoms from diffusing across [65].

Chapter 2. Nucleation and Growth of Dendritic Islands during Platinum Oxidation-Reduction Cycling

Even if the spoke-wheels are distorted, like in Fig. 2.2b, a PtO_2 -adatom can only “escape” from a triangle if it finds the open pathway between the spokes. This requires a significant amount of time, as the PtO_2 -adatom needs several attempts during its random walk to find this open path. Even if nucleation is thermodynamically favourable, it will take quite a long time to occur. This limited diffusion also extremely hinders mass transport between the terrace sites and the kinks, thus preventing a quick equilibration of the chemical potentials and the required adatom concentration.

If we now consider that the critical nucleation *cluster* would be a single adatom, meaning that the smallest stable cluster would be a dimer, and that diffusion between triangles is fully prohibited, nucleation would only occur in those triangles that have received two PtO_2 -adatoms: thus in 50% of the triangles, as there is, on average, the formation of 1.5 PtO_2 -adatoms per triangle. In the case that a dimer would be the critical nucleus size, one additional PtO_2 -adatom would be needed for all the dimers to form a stable nuclei. As this only can come from neighboring triangular areas, a single PtO_2 -adatom has to “escape” its own triangular area, finding its way through the open paths between the spokes. Statistically, this would lead to every second triangle with a stable trimer, while the others would not have any adatom.

Once the spokes reduce during the broad cathodic peak at around 0.8 V (see Fig. 2.1), the PtO_2 -adatoms can freely diffuse over the Pt(111) terrace, although, as commented before, only with 0.28 jumps/s (compare to the Pt-adatoms with 10^8 jumps/s). Therefore, even though below 0.94 V $\theta_{eq, \text{PtO}_2, ad}$ (3) has decreased such that now $\theta_{\text{PtO}_2, ad}$ is larger (i.e. $\theta_{\text{PtO}_2, ad} = 0.0245$, as this is the flux of PtO_2 -adatoms created during the PE_{irr} [80]), nucleation will not occur within the time needed to reach 0.59 V during the cathodic scan. At 0.59 V, the PtO_2 -adatoms reduce to Pt-adatoms, which probably explains the cathodic peak starting at around this potential. As the Pt-adatoms diffuse with 10^8 hops per second, instant nucleation occurs. Interestingly, Wakisaka et al. reported that they could not observe the islands until the potential was reduced to 0.49 V [24], which would point out that Pt-adatoms, and not PtO_2 -adatoms, are the species involved during nucleation.

Due to the non-random character of both the PE_{rev} and the PE_{irr} processes, the islands resulting from the nucleation are distributed within a certain distance to each other, as observed in Ref. [65]. More concretely, there are two possible reasons for this. The first one is that the PtO_2 -adatoms are formed within a certain distance between each other, therefore leading also (statistically) to nuclei with a homogeneous distance distribution. The second one is that the PtO_2 -adatoms are retained so long within their triangular areas of origin that, once the spokes are reduced, the statistical distance between the PtO_2 -adatoms is equal and thus, on average, all PtO_2 -adatoms need the same number of local random walks on the surface before a nucleation event occurs. Once the islands are formed, processes such as Ostwald ripening (i.e. atom diffusion from the smaller to the larger islands) and/or Smoluchowski ripening (i.e. smaller islands diffusing as a whole unit and getting incorporated into the larger, less mobile islands nearby) become important [101–103], and result in a larger averaged island size at the expense of a lower island density.

2.5 Dendritic Islands and their Step Length




Figure 2.6: Dendritic Islands on Pt(111). (a) Vacuum-STM image of dendritic islands formed after a potential step from 1.0 to 1.3 V, holding 1.3 V for 10 s, and stepping back to 1.0 V before finally sweeping to 0.05 V at 50 mV/s. The image is reproduced with permission from T. Maagaard [40]. (b), (c) and (d) are the upper, the best, and the lower estimate, respectively, of the area of the island marked with a red square in (a). (e) Dendritic islands observed with our EC-STM after holding the potential at 1.35 V for 200 s, and then reducing to 0.3 V with 25 mV/s. This image was recorded by L. Jacobse, with $U_s = 300$ mV, $U_t = 310$ mV, and $I_t \approx 300$ pA. (f), (g) and (h) are the respective upper, best, and lower estimate of the area of the island marked in red in (e).

Figure 2.6a shows an STM image (reproduced with permission from [40]) of islands created by stepping the potential from 1.0 V to 1.3 V and holding it there for 10 seconds, before stepping back to 1.0 V, and finally sweeping with 50 mV/s to 0.05 V to completely reduce the oxide. Subsequently, the Pt(111) sample was taken out of the electrolyte, dried, and

Chapter 2. Nucleation and Growth of Dendritic Islands during Platinum Oxidation-Reduction Cycling

mounted inside a vacuum-STM chamber to perform the imaging. Interestingly, the islands created in this way are dendritic, and not hexagonal as reported in the EC-STM study in Ref. [26].

Figure 2.6e shows an EC-STM image (taken in the electrolyte) of the islands formed by sweeping the potential from 0.3 to 1.35 V at 25 mV/s and holding it there during 200 s before sweeping back to 0.3 V at 25 mV/s to reduce the oxide. Upon closer inspection, one can see that also these islands are dendritic in shape, although more compact than the ones measured in vacuum (compare with Fig. 2.6a).

The origin of the dendritic islands requires a growth instability that is caused by the Kink Ehrlich-Schwoebel Effect (KESE). The reason for this energetic barrier is manifested in the lower coordination of an atom diffusing around a kink when it is at the transition state. Its similarity with the one dimensional higher (3D instead of 2D) Ehrlich-Schwoebel barrier [81, 82] was realized for the first time by Pierre-Louis [104, 105]. Figure 2.7 sketches the general mechanism for the formation of dendritic islands. The arrival of adatoms to an island edge, given by a step, leads to the nucleation of a 1D island step-row (in full similarity to island nucleation on a terrace). In analogy to mound formation in 3D [80, 106], these 1D islands grow in the perpendicular direction to the step, because of the limited diffusion around the kinks introduced by the KESE. The faster the arrival of the adatoms (i.e. the higher the flux) towards the island edge, the higher the growth speed becomes in the perpendicular direction to the step. As the diffusion barriers are flux independent, this implies that there is less time for the arriving atoms to try hopping around the corner and thus overcoming the KESE. In other words, the remaining growing triangles do become shorter at their base, and it might be even possible to nucleate two 1D rows, thus two triangles, at one step edge. Therefore, a sudden large flux of adatoms that are released during the reduction of the PtO_2 -adatoms significantly favors the formation of even smaller branches that are characteristic for the dendritic shape. Once these branches are formed, they ramify by the incorporation of new adatoms to the edges of the branches, thus once again forming 1D islands that grow.

The island shape, especially the ratio of the perimeter to area and thus also the ratio of step sites to terrace sites, crucially effects the ORR activity as well as the catalyst degradation [107, 108]. Calle-Vallejo et al. [1] reported that the ORR activity measured at 0.9 V increased more than three times after roughening a Pt(111) electrode by performing 10 ORCs up to 1.72 V, which is likely below the 2D to 3D transition growth state of the islands [25].

In order to measure the perimeter and the area of the dendritic islands, we first need to delimit the island boundaries. This is far from trivial, as STM images suffer inherently from tip convolution, which is more severe the smaller the feature sizes and the larger the tip radius. Realizing the dendritic island shape with its tiny branches, we obviously need a careful approach for the proper determination of the perimeter. The approach chosen for the analysis and the effect of tip convolution could be the reason why in Ref. [26] it was suggested that the islands were hexagonal.

Starting with the more branched islands measured in vacuum, we decided to define an upper, best, and lowest estimate of the island area, as shown for the particular example dis-




Figure 2.7: Scheme of the Growth Instability (KESE) resulting in Dendritic Islands: (a) Step-adatom (1D) diffusion resulting in the nucleation of 1D-island rows. (b) The KESE makes it more difficult for the atom to diffuse around the kink, leading to the nucleation and growth of a second row (c). (d) The arrival of more adatoms leads eventually to the growth of triangles (branches) perpendicular to the step. (e) Nucleation of a new row on the side of a triangle, which finally results in the bifurcation of the branch (f).

played in Fig. 2.6(b-d). In order to determine the different estimates, we first changed the color scale to gray scale, which delivers higher contrast. Then, using a threshold routine that displays everything above the threshold in white and below in black, we generated the images. The upper estimate was generated by decreasing the threshold until the shallow trenches within the island were almost filled (note the trench indicated with the orange arrow in Fig. 2.6b as an example). For the lower estimate, we increased the threshold until one of the parts clearly forming the island almost disappeared (see the part marked with the orange arrow in Fig. 2.6d). This lower estimate ensures that we account also for tip deconvolution. In the best estimate, which is the one used in the further analysis, we adjusted the island area as accurate as possible to the upper part of the island (step) height. The upper, the best, and the lowest estimates of the area of the islands measured in electrolyte were obtained in the same way (see Fig. 2.6(f-h) as an example).

To quantify the degree of the dendritic shape, we defined a roughness factor of the island edge (ϵ_r) as follows:

$$\epsilon_r = \frac{L_{dendritic}}{L_{circular}} \quad (2.9)$$

Chapter 2. Nucleation and Growth of Dendritic Islands during Platinum Oxidation-Reduction Cycling

where $L_{dendritic}$ is the perimeter (step length) of the dendritic island in the best estimate and $L_{circular}$ is the perimeter of a circular island of exactly the same area, calculated as:

$$L_{circular} = 2\sqrt{\pi A} \quad (2.10)$$

where A is the area of the dendritic island in the best estimate.

Figure 2.8 shows the statistical distributions of ϵ_r obtained from analyzing 200 islands imaged in vacuum (a) and 250 islands imaged in the electrolyte (b). The maximum in the fit of the ϵ_r distribution for the vacuum measurement has a higher value, $\epsilon_r = 1.96$, than the maximum in the fit of the ϵ_r distribution for the measurement in electrolyte, $\epsilon_r = 1.63$. One possible explanation for this is that the STM resolution at the island edges is lower in electrolyte than in vacuum, as the work function is approximately three times larger in the latter case [44]. One could try to compensate this effect by increasing the tunneling current, hence decreasing the distance between tip and sample, but this would also lead to a worse signal-to-noise and more instabilities in the feedback loop of the STM, as the same mechanical noise would be also exponentially increased. Next to this purely technical reason, the precise experimental details for the island creation also determines the degree of the dendritic shape and thus the measured ϵ_r , as we explain in the following.

The size of the islands is dictated by the ratio F/M that was described in the Introduction. A higher flux leads to smaller islands, while a higher mobility leads to larger islands [17, 25, 80]. While both the higher upper potential and the longer oxidation time, for the EC-STM measurements, result in a larger effective flux, the slower scan rate during the cathodic sweep results in a higher mobility (i.e. the adatoms have more time to diffuse before nucleating into islands). As becomes clear from the above, these two effects point towards opposite directions: a decrease and an increase, respectively, of the island area. However, by comparing the islands in Fig. 2.6a with the ones in Fig. 2.6e, one can see that the latter are significantly smaller (note the different image sizes), and therefore, the increase of the upper potential and the oxidation time must outweigh the higher mobility introduced by slower sweeping. Smaller islands are more difficult to analyze accurately than larger ones, recall the above explained tip convolution. This leads to a lower measured ϵ_r , as the small scale roughness at the island edges can not easily be captured. As explained before, the faster the arrival of adatoms towards the island edge, the more pronounced the dendritic growth becomes. Therefore, a faster scan rate during the cathodic sweep, and thus faster reduction of the PtO₂-adatoms to Pt-adatoms (which have a higher diffusion rate) results in a larger ϵ_r .

As delimiting the island edges is subject to error, we used the three estimates measured for each island to calculate the lower and upper errors of ϵ_r . This was done by dividing, respectively, the smallest perimeter with the largest area, and the largest perimeter with the smallest area, before averaging over all the islands. This resulted in a lower and an upper error of 23 % and 25 %, respectively, for the islands measured in vacuum. For the islands measured in electrolyte, we found an upper and lower error of 21 % and 30 %, respectively. Realizing both upper and lower errors, one could argue that there is no difference in the ϵ_r between both measurements, as the difference in the two peak maximum values falls within this error margin. This is clearly observed in Fig. 2.8, where both upper and lower




Figure 2.8: Statistical Distribution of ϵ_r for the Best Estimate of the Island Shapes: (a) measured in vacuum (analyzed from Fig. 2.6a and Fig. A.3 in the Appendix A) and (b) in electrolyte (analyzed from Fig. 2.6e and Fig. A.5 in Appendix A). The peak maximum of the statistical distributions, obtained by fitting with a Pearson IV function, are indicated with red dashed lines. The lower and upper bound are indicated with the orange arrow, while the statistical error, derived via the possible shift within the statistical error bars, is indicated with the green arrow.

boundaries are shown. However, the upper and lower bounds are larger than the natural statistical error that is given by the shifts of the distribution of ϵ_r to the left and to the right,

Chapter 2. Nucleation and Growth of Dendritic Islands during Platinum Oxidation-Reduction Cycling

taking into account the error of $\sqrt{N}$, where N is the number of counts for each bin. This is not surprising, as the upper and lower bounds describe the maximum total errors. The statistical errors, however, intrinsically project the real randomness of the island shape. Considering this last error for both measurements, we conclude that, although there is a difference between the two peak maximum values of ϵ_r , the difference is very small: while the peak of ϵ_r from the measurement in vacuum (a) could be shifted down to 1.81, it could be shifted up to 1.7 in the measurement in the electrolyte (b), thus only 0.11 difference between them.

In order to study further not only the effect of the experimental oxidation-reduction conditions chosen, but also the evolution of the island shape during growth, we created islands by performing ORCs between 0.06 V and 1.35 V and at 50 mV/s (see Fig. 2.9). We then obtained the distributions of ϵ_r of the adatom islands after 1, 6 and 7 ORCs (see Fig. 2.10), which we compared with the distribution of ϵ_r for the EC-STM measurement presented above in Fig. 2.6e, in which the potential was held at 1.35 V for 200 s.

The first we note is that all islands in Fig. 2.9(a-d) are dendritic, independently of the electrochemical treatment. The statistical distribution resulting from the potential hold experiment shows a larger ϵ_r value of 1.63 in comparison to the $\epsilon_r = 1.57$ on ORC #1. The reason for this is that, at longer waiting times, more PE_{irr} atoms are created [65, 71]. However, even if we handle the same “waiting” time, the distributions show that the islands become more compact with increasing ORC number: note the shift between ORC #1 and ORC #6, but also the slight shift to smaller values from ORC #6 to ORC #7. Although these shifts fall within the statistical errors of the distributions, and hence they should be treated with caution, this trend is what we would expect according to our understanding on the atomic details underlying island growth, as we explain in the following.

We have concluded earlier that above 0.8 V the steps oxidize, and that there is a large driving force to form PtO_2 -adatoms from the kinks. We have evidence that, in analogy to the PE_{irr} on the terrace, the oxide chains at the steps also push PtO_2 units up onto the upper terrace, thus becoming PtO_2 -adatoms. It was observed in Ref. [25] that the transition from 2D to 3D island growth (occurring between the 20th and the 30th ORC) results in a significant decrease in the growth exponent. This can only be explained by a pronounced decrease of the flux, which can only be due to a change in the roughening (growth) mechanism [109]. The flux has two contributions, the PE_{irr} atoms created on the terraces, and the PtO_2 -adatoms formed by oxidizing the steps. The mechanism in which the latter takes place could be similar to the PE_{rev} and the PE_{irr} on a terrace: it starts with lifting PtO_2 units (PE_{rev} atoms) along the step and, once a critical stress along the step-row is reached, one unit per certain row length is pushed onto the upper terrace. While the terrace width decreases considerably as the growth transitions from 2D to 3D, becoming as small as 2 platinum distances [26], the step density increases to its maximum. Therefore, the decrease in the flux must be due to the change of these two contributions. However, as the roughening (growth) continues to at least up to 170 cycles and the terraces in the 3D mounts can not accommodate the oxide spokes, the dominating flux of PtO_2 -adatoms during the late stages of growth must come from the steps. Furthermore, as the growth of the mounts occurs predominantly in height, the PtO_2 -adatom flux from the steps must go uphill.




Figure 2.9: Degree of Dendritic Island Shape as Function of ORC-number. (a) As a reference, after holding the potential at 1.35 V for 200 s before reducing to 0.3 V with 25 mV/s. (b) After the first ORC between 0.06 V and 1.35 V. (c) After 6 ORCs. (d) After 7 ORCs. All ORCs are performed with a scan rate of 50 mV/s. All images are $80 \times 80 \text{ nm}^2$. Larger scale images are provided in Appendix A.

Coming back to the explanation for the decrease of ϵ_r upon cycling, the uphill flux from the steps results in PtO_2 -adatoms on the island. These PtO_2 -adatoms (or Pt-adatoms, upon reduction), instead of nucleating, hop down the step and get incorporated to the island edge. This is because the Ehrlich-Schwoebel barrier vanishes for small terrace widths [83–85], like on the branches. Consequently, the “fjords” between the branches get filled, leading to more compact shapes. This “annealing” is repeated during each ORC and competes with the dendritic growth in the perpendicular direction of the step. If the filling of the fjords is faster than the dendritic growth, ϵ_r will decrease after each cycle, meaning that

Chapter 2. Nucleation and Growth of Dendritic Islands during Platinum Oxidation-Reduction Cycling

the islands become more compact.

Finally, another cause for the decrease of ϵ_r upon cycling originates from the increase of the island perimeter upon growth. As this leads to longer steps with less kinks, the KESE becomes less relevant for the step-adatom diffusion along the island edge: the step-adatoms have more distance to diffuse along the step before finding a kink. This leads to an increase of the width of the branches at their base (see Fig. 2.7), and hence less dense branching, which results in a lower ϵ_r .




Figure 2.10: Evolution of the Statistical Distributions of ϵ_r upon Oxidation-Reduction Cycling. (a) Comparison of the statistical distributions obtained from the measurement described before, in which the potential was held at 1.35 V for 200 s (blue dotted line), with the distributions obtained after 1, 6, and 7 ORCs, in green, orange and purple, respectively. The latter three distributions are also shown in (b), (c), and (d), respectively, where we also provide a curve fit to highlight the peak maximum, error bars based on the statistical error at each bin, and a green arrow representing the shift of the peak maximum due to the statistical error.

2.6 Conclusions

In this work, we have studied with DFT both the stability and the mobility of two different adatom species, Pt-adatom and PtO₂-adatom, on Pt(111) by calculating their formation energies and diffusion rates at different electrode potentials, with the aim to get a better understanding on the nucleation of adatom islands upon oxidation-reduction cycling. Our results show that, although during the forward (anodic) scan the irreversible place-exchange that starts at 1.17 V leads to the creation of PtO₂-adatoms, nucleation into PtO₂-islands does not occur. The reason for this is that the equilibrium concentration of PtO₂-adatoms reaches practically 1 ML at 0.94 V, and thus at these high potentials the complete surface prefers to be oxidized. Nucleation into PtO₂-adatom islands does not occur with ORCs even up to 1.35 V, as there are only 0.0245 ML PtO₂-adatoms created during the irreversible place-exchange, which is significantly lower than 1 ML. During the subsequent cathodic scan, the equilibrium concentration of PtO₂-adatoms decreases exponentially with the potential and, below 0.94 V, it becomes lower than the actual PtO₂-adatom concentration of 0.0245 ML. Therefore, nucleation becomes thermodynamically favorable. However, the PtO₂-adatoms are “trapped” in between the oxide rows that are created during the reversible part of the oxidation. As these rows are lifted almost 1 ML high from the surface, nucleation is hindered by too low mobility. In addition, PtO₂-adatoms diffuse very slow, 0.28 jumps/s, and hence they do not have enough time to find each other before they reduce to Pt-adatoms. Pt-adatoms diffuse much faster (10⁸ jumps/s) and therefore, once they form at 0.59 V, they rapidly find each other and nucleate into adatom islands, as also their actual concentration is much higher than their equilibrium concentration. These results match the observations from Wakisaka et al. [24], who reported that the adatom islands do not form until the potential is decreased to 0.49 V.

As not only the electrocatalytic activity of platinum, but also its degradation is highly dependent on the concentration of the different surface sites, we also analyzed the shape of the islands formed from vacuum STM and EC-STM images. We quantified the island perimeter and the area to finally determine the island compactness and a factor that describes the additional step length with respect to a circular island. Contrary to what was suggested in the literature, the islands formed upon oxidation-reduction are dendritic, and not hexagonal, which matches the observations from MBE experiments in vacuum. Finally, we studied the shape evolution during the island growth upon oxidation-reduction cycling. Although within the statistical error bars of the distributions, we have indications that the dendritic islands change towards more compact shapes with increasing cycle number. This trend matches our insight into the atomic picture during growth and can be explained by: (1) the uphill flux originating from the island edges, and the downhill interlayer diffusion of adatoms that end up filling the “fjords” between the island branches; and (2) the longer step length for larger islands on which a step-adatom can diffuse without encountering a kink, leading to less branching and thus less dendritic growth.

References

- [1] F. Calle-Vallejo, J. Tymoczko, V. Colic, Q. Huy Vu, M. D. Pohl, K. Morgenstern, D. Lofreda, P. Sautet, W. Schuhmann, and A. S. Bandarenka, *Science*, **350**, 185 (2015).
- [2] T. Zambelli, J. Wintterlin, J. Trost and G. Ertl, *Science*, **273**, 1688 (1996).
- [3] K. J. P. Schouten, E. Pérez Gallent and M. T. M. Koper, *ACS Catal.*, **3**, 1292 (2013).
- [4] A. Kuzume, E. Herrero, and J. M. Feliu, *J. Electroanal. Chem.*, **599**, 333 (2007).
- [5] M.D. Maciá, J.M. Campiña, E. Herrero, and J.M. Feliu, *J. Electroanal. Chem.*, **564**, 141 (2004).
- [6] F. Xiao, Y. Wang, Z. Wu, G. Chen, F. Yang, S. Zhu, K. Siddharth, Z. Kong, A. Lu, J. Li, C. Zhong, Z. Zhou, and M. Shao, *Adv. Mater.*, **33**, 2006292 (2021).
- [7] J. K. Nørskov, J. Rossmeisl, A. Logadottir, L. Lindqvist, J. R. Kitchin, T. Bligaard, and H. Jónsson, *J. Phys. Chem. B*, **108**, 17886 (2004).
- [8] X. Tian, P. Zhao, and W. Sheng, *Adv. Mater.*, **31**, 1808066 (2019).
- [9] S. Wang, A. Lu, and C. Zhong, *Nano Convergence*, **8**, 4 (2021).
- [10] R. L. Borup, A. Kusoglu, K. C. Neyerlin, R. Mukundan, R. K. Ahluwalia, D. A. Cullen, K. L. More, A. Z. Weber, and D. J. Myers, *Curr. Opin. Electrochem.*, **21**, 192 (2020).
- [11] A. A. Topalov, S. Cherevko, A. R. Zeradjanin, J. C. Meier, I. Katsounaros, and K. J. J. Mayrhofer, *Chem. Sci.*, **5**, 631 (2014).
- [12] D. J. S. Sandbeck, O. Brummel, K. J. J. Mayrhofer, J. Libuda, I. Katsounaros, and S. Cherevko, *Chem. Phys. Chem.*, **20**, 2997 (2019).
- [13] D. J. S. Sandbeck, M. Inaba, J. Quinson, J. Bucher, A. Zana, M. Arenz, and S. Cherevko, *ACS Appl. Mater. Interfaces*, **12**, 25718 (2020).
- [14] F. T. Wagner and P. N. Ross, *Surf. Sci.*, **160**, 305 (1985).
- [15] H. You and Z. Nagy, *Physica B: Condens. Matter*, **198**, 187 (1994).
- [16] Z. Nagy and H. You, *Electrochim. Acta*, **47**, 3037 (2002).
- [17] M. Ruge, J. Drnec, B. Rahn, F. Reikowski, D. A. Harrington, F. Carlà, R. Felici, J. Stettner, and O. M. Magnussen, *J. Am. Chem. Soc.*, **139**, 4532 (2017).
- [18] N. Breuer, A. M. Funtikov, U. Stimming, and R. Vogel, *Surf. Sci.*, **335**, 145 (1995).
- [19] N. Furuya and M. Shibata, *J. Electroanal. Chem.*, **467**, 85 (1999).
- [20] S. Sugawara and K. Itaya, *J. Chem. Soc.*, **85**, 1351 (1989).
- [21] K. Itaya, S. Sugawara, K. Sashikata, and N. Furuya, *J. Vac. Sci. Technol. A*, **8**, 515 (1990).
- [22] K. Sashikata, N. Furuya, and K. Itaya, *J. Vac. Sci. Technol. B: Microelectron. Process. Phenom.*, **9**, 457 (1991).

- [23] Y. Sugawara, M. Sasaki, I. Muto, and N. Hara, *ECS Trans.*, **64**, 81 (2014).
- [24] M. Wakisaka, S. Asizawa, H. Uchida, and M. Watanabe, *Phys. Chem. Chem. Phys.*, **12**, 4184 (2010).
- [25] L. Jacobse, Y. F. Huang, M. T. M. Koper, and M. J. Rost, *Nat. Mater.*, **17**, 277 (2018).
- [26] L. Jacobse, M. J. Rost, and M. T. M. Koper, *ACS Cent. Sci.*, **5**, 1920 (2019).
- [27] G. Wulff, *Z. Krystallogr.*, **34**, 449 (1901).
- [28] C. Herring, *Phys. Rev.*, **82**, 87 (1951).
- [29] J. Ikononov, K. Starbova, H. Ibach, and M. Giesen, *Phys. Rev. B*, **75**, 245411 (2007).
- [30] T. Michely, M. Hohage, M. Bott, and G. Comsa, *Phys. Rev. Lett.*, **70**, 3943 (1993).
- [31] R. F. Sekerka, *Cryst. Res. Technol.*, **740**, 291 (2005).
- [32] W. W. Mullins and R. F. Sekerka, *J. Appl. Phys.*, **34**, 323 (1963).
- [33] S. Ogura, K. Fukutani, M. Matsumoto, T. Okano, M. Okada, and T. Kawamura, *Phys. Rev. B*, **73**, 125442 (2006).
- [34] R. Q. Hwang, J. Schröder, C. Günther, and R. J. Behm, *Phys. Rev. Lett.*, **67**, 3279 (1991).
- [35] Z. Zhang and M. Lagally, *Science*, **276**, 377 (1997).
- [36] Z. Zhang, X. Chen, and M. Lagally, *Phys. Rev. Lett.*, **73**, 1829 (1994).
- [37] T. Michely and J. Krug, *Islands, Mounds and Atoms*, Springer, Amsterdam (2004).
- [38] M. Bott, T. Michely, and G. Comsa, *Surf. Sci.*, **272**, 161 (1992).
- [39] M. Hohage, M. Bott, M. Morgenstern, Z. Zhang, T. Michely, and G. Comsa, *Phys. Rev. Lett.*, **76**, 2366 (1996).
- [40] T. Maagaard, PhD thesis (2018), Department of Physics, Danmarks Tekniske Universitet (DTU), Denmark, <<https://orbit.dtu.dk/en/publications/combining-uhv-stm-and-electrochemistry-for-surface-studies-of-mod>>.
- [41] J. Drnec, M. Ruge, F. Reikowski, B. Rahn, F. Carlà, R. Felici, J. Stettner, O. M. Magnussen, and D. A. Harrington, *Electrochim. Acta*, **224**, 220 (2017).
- [42] M. J. Rost, L. Crama, P. Schakel, E. van Tol, G. B. E. M. van Velzen-Williams, C. F. Overgaw, H. ter Horst, H. Dekker, B. Okhuijsen, M. Seynen, A. Vijftigschild, P. Han, A. J. Katan, K. Schoots, R. Schumm, and W. van Loo, *Rev. Sci. Instrum.*, **76**, 053710 (2005).
- [43] Y. I. Yanson, F. Schenkel, and M. J. Rost, *Rev. Sci. Instrum.*, **84**, 023702 (2013).
- [44] M. J. Rost, in *Encyclopedia of Interfacial Chemistry*, 1st ed., K. Wandelt, p.180, Elsevier, Amsterdam (2018).
- [45] M. J. Rost, G. J. C. van Baarle, A. J. Katan, W. M. van Spengen, P. Schakel, W. A. van Loo, T. H. Oosterkamp, and J. W. M. Frenken, *Asian J. Control*, **11**, 110 (2009).

Chapter 2. Nucleation and Growth of Dendritic Islands during Platinum Oxidation-Reduction Cycling

- [46] G. Kresse and J. Furthmüller, *Phys. Rev. B.*, **54**, 169 (1996).
- [47] G. Kresse and J. Furthmüller, *Comput. Mater. Sci.*, **6**, 15 (1996).
- [48] G. Kresse and J. Hafner, *Phys. Rev. B.*, **47**, 558, (1993).
- [49] J. P. Perdew, J. A. Chevary, S. H. Vosko, K. A. Jackson, M. R. Pederson, D. J. Singh, and C. Fiolhais, *Phys. Rev. B.*, **46**, 6671 (1992).
- [50] Kittel, C., *Introduction to Solid State Physics*, 7th edn., Wiley, New York (2008).
- [51] H. J. Monkhorst and J. D. Pack, *Phys. Rev. B.*, **13**, 5188 (1976).
- [52] L. Bengtsson, *Phys. Rev. B.*, **59**, 12302 (1999).
- [53] I. T. McCrum, M. A. Hickner, and M. J. Janik, *Langmuir*, **33**, 7043 (2017).
- [54] D. Fantauzzi, J. Bandlow, L. Sabo, J. E. Mueller, A. C. T. van Duin, and T. Jacob, *Phys. Chem. Chem. Phys.*, **16**, 23118 (2014).
- [55] G. Henkelman, B. P. Uberuaga, and H. Jónsson, *J. Chem. Phys.*, **113**, 9901 (2000).
- [56] J. Clavilier, K. El Achi, and A. Rodes, *J. Electroanal. Chem.*, **272**, 253 (1989).
- [57] A. Rodes, K. El Achi, M. A. Zamakhchari, and J. Clavilier, *J. Electroanal. Chem.*, **284**, 245 (1990).
- [58] X. Chen, I. T. McCrum, K. A. Schwarz, M. J. Janik, and M. T. M. Koper, *Angew. Chem. Int. Ed.*, **56**, 15025 (2017).
- [59] M. J. T. C. van der Niet, N. Garcia-Araez, J. Hernández, J. M. Feliu, and M. T. M. Koper, *Catal. Today*, **202**, 105 (2013).
- [60] R. Rizo, J. Fernández-Vidal, L. J. Hardwick, G. A. Attard, F. J. Vidal-Iglesias, V. Climent, E. Herrero, and J. M. Feliu, *Nat. Commun.*, **13**, 2550 (2022).
- [61] A. Björling, E. Ahlberg, and J. M. Feliu, *Electrochem. Commun.*, **12**, 359 (2010).
- [62] A. Björling, E. Herrero, and J. M. Feliu, *J. Phys. Chem.*, **115**, 15509 (2011).
- [63] F. T. Wagner and P. N. Ross, *J. Electroanal. Chem.*, **250**, 301 (1998).
- [64] H. Tanaka, S. Sugawara, K. Shinohara, T. Ueno, S. Suzuki, N. Hoshi, and M. Nakamura, *Electrocatalysis*, **6**, 295 (2015).
- [65] M. J. Rost, L. Jacobse, and M. T. M. Koper, *Angew. Chem. Int. Ed.*, **62**, e202216376 (2023).
- [66] M. A. H. Lanyon and B. M. W. Trapnell, *Proc. R. Soc. A.*, **227**, 387 (1955).
- [67] A. K. N. Reddy, M. A. Genshaw, and J. O. Bockris, *J. Chem. Phys.*, **48**, 671 (1968).
- [68] K. J. Vetter and J. W. Schultze, *J. Electroanal. Chem.*, **34**, 141 (1972).
- [69] B. V. Tilak, B. E. Conway, and H. Angerstein-Kozłowska, *J. Electroanal. Chem.*, **48**, 1 (1973).

- [70] G. Jerkiewicz, G. Vatankhah, J. Lessard, M. P. Soriaga, and Y. Park, *Electrochim. Acta*, **49**, 1451 (2004).
- [71] L. Jacobse, V. Vonk, I. T. McCrum, C. Seitz, M. T. M. Koper, M. J. Rost, and A. Stierle, *Electrochim. Acta*, **407**, 139881 (2022).
- [72] M. Ruge, J. Drnec, B. Rahn, F. Reikowski, D. A. Harrington, F. Carlà, R. Felici, J. Stettner, and O. M. Magnussen, *J. Electrochem. Soc.*, **164**, H608 (2017).
- [73] A. Björling and J. M. Feliu, *J. Electroanal. Chem.*, **662**, 17 (2011).
- [74] A. M. Gómez-Marín and J. M. Feliu, *Electrochim. Acta*, **82**, 558 (2012).
- [75] A. M. Gómez-Marín and J. M. Feliu, *Electrochim. Acta*, **104**, 367 (2013).
- [76] A. M. Gómez-Marín, J. Clavilier, and J. M. Feliu, *J. Electroanal. Chem.*, **688**, 360 (2013).
- [77] J. Drnec, M. Ruge, F. Reikowski, B. Rahn, F. Carlà, R. Felici, J. Stettner, O. M. Magnussen, and D. A. Harrington, *Electrochem. Commun.*, **84**, 50 (2017).
- [78] H. You, D. J. Zurawski, Z. Nagy, and R. M. Yonco, *J. Chem. Phys.*, **100**, 4699 (1994).
- [79] Y. Liu, A. Barbour, V. Komanicky, and H. You, *J. Phys. Chem. C*, **120**, 16174 (2016).
- [80] M. J. Rost, L. Jacobse, and M. T. M. Koper, *Nat. Commun.*, **10**, 5233 (2019).
- [81] G. Ehrlich and F. G. Hudda, *J. Chem. Phys.*, **44**, 1039 (1966).
- [82] R. L. Schwoebel and E. J. Shipsey, *J. Appl. Phys.*, **37**, 3682 (1966).
- [83] M. Giesen, G. S. Icking-Konert, and H. Ibach, *Phys. Rev. Lett.*, **82**, 3101 (1999).
- [84] M. Giesen and H. Ibach, *Surf. Sci. Lett.*, **464**, L697 (2000).
- [85] K. Morgenstern, G. Rosenfeld, G. Comsa, M. R. Sørensen, B. Hammer, E. Lægsgaard, and F. Besenbacher, *Phys. Rev. B*, **63**, 045412 (2001).
- [86] M. A. van Spronsen, J. W. M. Frenken, and I. M. N. Groot, *Nat. Commun.*, **8**, 429 (2017).
- [87] S. Hanselman, I. T. McCrum, M. J. Rost, and M. T. M. Koper, *Phys. Chem. Chem. Phys.*, **22**, 10634 (2020).
- [88] H. Ibach, *Physics of Surfaces and Interfaces*, Springer, Amsterdam (2006).
- [89] J. G. Wang, W. X. Li, M. Borg, J. Gustafson, A. Mikkelsen, T. M. Pedersen, E. Lundgren, J. Weissenrieder, J. Klikovits, M. Schmid, B. Hammer, and J. N. Andersen, *Phys. Rev. Lett.*, **95**, 256102 (2005).
- [90] J. Bandlow, P. Kaghazchi, and T. Jacob, *Phys. Rev. B*, **83**, 174107 (2011).
- [91] J. Lapujoulade, *Surf. Sci. Rep.*, **20**, 191 (1994).
- [92] M. J. Rost, S. B. van Albada, and J. W. M. Frenken, *Surf. Sci.*, **518**, 21 (2002).
- [93] M. J. Rost, S. B. van Albada, and J. W. M. Frenken, *Europhys. Lett.*, **59**, 559 (2002).

Chapter 2. Nucleation and Growth of Dendritic Islands during Platinum Oxidation-Reduction Cycling

- [94] M. J. Rost, S. B. van Albada, and J. W. M. Frenken, *Surf. Sci.*, **515**, 344 (2002).
- [95] M. J. Rost, S. B. van Albada, and J. W. M. Frenken, *Surf. Sci.*, **547**, 71 (2003).
- [96] V. Climent, G. A. Attard, and J. M. Feliu, *J. Electroanal. Chem.*, **532**, 67 (2002).
- [97] K. Ojha, N. Arulmozhi, D. Aranzales, and M. T. M. Koper, *Angew. Chem.*, **130**, 721 (2020).
- [98] M. Bott, M. Hohage, M. Morgenstern, T. Michely, and G. Comsa, *Phys. Rev. Lett.*, **76**, 1304 (1996).
- [99] K. Kyuno and G. Ehrlich, *Surf. Sci.*, **437**, 29 (1999).
- [100] P. Stoltze, *J. Phys.: Condens. Matter.*, **6**, 9495 (1994).
- [101] K. Morgenstern, G. Rosenfeld, E. Lægsgaard, F. Besenbacher, and G. Comsa, *Phys. Rev. Lett.*, **80**, 556 (1998).
- [102] K. Morgenstern, G. Rosenfeld, and G. Comsa, *Phys. Rev. Lett.*, **76**, 2113 (1996).
- [103] G. Rosenfeld, K. Morgenstern, M. Esser, and G. Comsa, *Appl. Phys. A*, **69**, 489 (1999).
- [104] O. Pierre-Louis, M. R. D’Orsogna, and T. L. Einstein, *Phys. Rev. Lett.*, **82**, 3661 (1999).
- [105] C. Misbah, O. Pierre-Louis, and Y. Saito, *Rev. Mod. Phys.*, **82**, 981 (2010).
- [106] M. J. Rost, *Phys. Rev. Lett.*, **99**, 266101 (2007).
- [107] B. Lim, M. Jiang, P. H. C. Camargo, E. C. Cho, J. Tao, X. Lu, Y. Zhu, and Y. Xia, *Science*, **324**, 1302 (2009).
- [108] G. Zhang, S. Sun, M. Cai, Y. Zhang, R. Li, and X. Sun, *Sci. Rep.*, **3**, 1526 (2013).
- [109] P. Meakin, *Fractals, Scaling and Growth Far from Equilibrium*, Cambridge University Press, Cambridge (1998).